


PRODUCT DATA SHEET  
Edition 07.2017 (06.2014)

# Sikafloor® Marine KG-202 N

## LIGHTWEIGHT PRIMARY DECK-COVERING MORTAR

Technical Data		Polymer-Modified Cement Mortar
Chemical Base		Grey
Colour		Hydraulic
Cure Mechanism		4.2 to 5.1 L
Mixing Ratio with cold, potable water	per 17 kg bag	1.1 g/cm <sup>3</sup> approx
Density freshly mixed (CQP <sup>1</sup> 599-3)		0.9 g/cm <sup>3</sup> approx
Density cured <sup>2</sup> (CQP 599-4)		5 to 35 °C
Substrate Temperature		8 to 100 mm
Application Thickness		18 m <sup>2</sup> approx
Coverage per 20 kg bag (1 mm layer thickness)		30 minutes approx
Working Time <sup>3</sup> (CQP 599-9)		10 hours approx
Ready for Foot Traffic <sup>3</sup> (CQP 600-3) (dependent upon humidity and ventilation)		12 MPa approx
Compressive Strength <sup>4</sup> (CQP 599-2)		5 MPa approx
Flexural Strength <sup>4</sup> (CQP 599-1)		2.9 GPa approx
Modulus of Elasticity in Compression <sup>4</sup> (CQP 599-6)		0.03% approx
Linear Shrinkage <sup>4</sup> (CQP 599-5)		12 months
Shelf Life (CQP 600-1) Stored in a cool, dry place below 25 °C		
<sup>1</sup> CQP = Corporate Quality Procedure; <sup>2</sup> After 7 days; <sup>3</sup> 23 °C and 50 % Relative Humidity; and <sup>4</sup> After 28 days.		
<b>Description</b>	Sikafloor® Marine KG-202 N is a one-component, light-weight levelling mortar based on polymer-modified cement. Sikafloor® Marine KG-202 N is manufactured in accordance with ISO 9001/14001 Quality Assurance Systems and tested according to the FTP Code system and approved according to the IMO Marine Equipment Directives.	
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>▪ Lightweight levelling mortar;</li> <li>▪ Low E-Modulus;</li> <li>▪ One-component, ready-to-mix;</li> <li>▪ Easy-to-apply;</li> <li>▪ Suitable for sloped surfaces;</li> <li>▪ Pumpable.</li> </ul>	
<b>Aeras of Application</b>	Sikafloor® Marine KG-202 N is applied on interior decks to level surfaces prior to applying deck coverings such as carpets, tiles, parquet, rubber and vinyl. It is suitable for application in dry and wet areas. For wet accommodation areas, prior to the application of tiles, the substrate must be treated with a water resistant membrane (e.g. Sikafloor® Marine Elastic). Before applying vinyl or carpet, it is recommended that a thin, self-levelling layer of mortar, such as Sikafloor® Marine-100, be applied to level the floor. This product is suitable for professional experienced users only. Tests with actual substrates under actual conditions must be performed to ensure adhesion and material compatibility.	
<b>Cure Mechanism</b>	Sikafloor® Marine KG-202 N is a hydraulic cement.	



---

**METHOD OF APPLICATION**

<b>Surface Preparation</b>	The surface must be clean and free from dust, grease, oils and other substances which may impair adhesion. Rust must be removed with a steel brush or other appropriate means, followed by vacuum cleaning. The surface must be primed with Sikafloor® Marine Primer-C using a long-haired roller. After the Primer has dried, the Sikafloor® Marine KG-202 N may be applied. For the application of Sikafloor® Marine KG-202 N on aluminium or zinc-rich shop primer-coated decks, a tie-coat of Sika ZP-Primer or other suitable tie-coat is required prior to the application of the Sikafloor® Marine Primer-C. For further information, contact the Technical Services Department of Sika Industry.
<b>Mixing Process</b>	Each bag of Sikafloor® Marine KG-202 N is mixed with approximately 4.2 to a maximum of 5.1 litres of cold potable water. The mixing time is approximately 3 minutes at low speed with a low-speed drill or with a cement mixer for larger amounts, until a homogeneous mortar is obtained. If mixed by hand, ensure that the powder is mixed completely (including bottom and side walls of the pail).
<b>Application</b>	Apply the mortar with a steel board or a straight-edge within 30 minutes of mixing. At temperatures above 35 °C, the Working Time will be reduced to 10 minutes or less. For advice on selecting and setting up a suitable pump system, please contact the System Engineering Department of Sika Industry.
<b>Curing</b>	Following application and during the curing process, the finished areas should be protected from direct heat (e.g. cutting or welding from beneath), sunlight and draft for at least one day. Before covering Sikafloor® Marine KG-202 N with dense materials such as vinyl or epoxy coatings, etc., ensure that the remaining moisture level is below 4%. Test procedure to determine the dryness (according to ASTM D 4263): -Put a PE-plastic foil 1 m x 1 m on the surface of the applied mortar floor; -Tape the perimeter and leave for one day. Curing is complete when there is no water condensation on the foil or visible colour difference between the covered and uncovered surfaces.
<b>Removal</b>	Excess material can best be removed before cure with a trowel wipe. Uncured Sikafloor® Marine KG-202 N may be removed from tools and equipment with water. Once cured, the material can only be removed mechanically. Exposed hands and skin should be washed immediately with water. Use suitable skin-protection hand cream.
<b>Further Information</b>	Copies of the following publications are available upon request: <ul style="list-style-type: none"><li>▪ <i>Safety Data Sheet</i></li><li>▪ <i>Application Guide Sikafloor® Marine KG-202 N</i></li></ul>
<b>Packaging</b>	17 kg bags.
<b>Value Bases</b>	All technical data stated in this Product Data Sheet are laboratory test-based. Current measured values may vary due to factors beyond our influence.
<b>Health and Safety Information</b>	For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN  
FOR INDUSTRIAL USE ONLY

---

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: [www.sika.ca](http://www.sika.ca)

**SIKA CANADA INC.****Head Office**

601, avenue Delmar  
Pointe-Claire, Quebec  
H9R 4A9

**Other locations**

Toronto  
Edmonton  
Vancouver

**1-800-933-SIKA**  
**[www.sika.ca](http://www.sika.ca)**

An ISO 9001 certified company  
Pointe-Claire: ISO 14001 certified EMS