

**Product Data Sheet**

Edition 08.2016/v1

CSC Master Format™ 03 05 00

Sika® Sigunit® L-50 AF

# Sika® Sigunit® L-50 AF

## Liquid Alkali-Free Shotcrete Accelerator

<b>Description</b>	Sika® Sigunit® L-50 AF is a high-performance, liquid, alkali-free accelerator for wet or dry shotcrete.	
<b>Where to Use</b>	<ul style="list-style-type: none"> <li>■ High quality and high initial strength shotcrete for general construction work.</li> <li>■ Support at the face and securing of rock in tunnel and mine construction.</li> <li>■ Rock and slope stabilisation along highways and transportation routes.</li> </ul>	
<b>Advantages</b>	<ul style="list-style-type: none"> <li>■ Alkali-free, avoiding additional leaching and pollution of alkalis and pollution of ground and surface water.</li> <li>■ When correctly used, marginal reduction of shotcrete strength.</li> <li>■ Reduction of rebound.</li> <li>■ Easier overhead spraying by improved bond of shotcrete to rock and concrete.</li> <li>■ Reduction of dust formation.</li> <li>■ Chloride-free, suitable for steel reinforced shotcrete and substrates.</li> </ul>	
	<b>Typical Data</b>	
	<b>Packaging</b>	1040 L IBC Totes and in bulk
	<b>Colour and Form</b>	Off White
	<b>Shelf Life and Storage</b>	At least three (3) months when stored in unopened, undamaged container in dry conditions, protected from sun and weather. Store at between 5 - 35°C (41 - 95°F).
	<b>Application Temperatures</b>	Concrete temperatures should not be lower than 15°C (59°F) (especially in cases of thick shotcrete layers). Lower temperatures will require higher dosages.
	<b>Properties</b>	
	<b>Dry matter content in solution</b>	45%
	<b>Density (of solution)</b>	1.36 kg/L
	<b>Chloride Content</b>	No added chlorides
	<b>Water soluble chloride (Cl), weight - %</b>	< 0.15

**How to Use****Dosage**

The exact dosage must be determined by preliminary testing. The dosage of Sika® Sigunit® L-50 AF, should be between 5 - 10% by weight of the cement. Lower temperatures will require higher dosages.

The set accelerating effect of Sigunit® L-50 AF depends on cement content, age, type and substrate. It is also dependent on the temperature of the shotcrete and the application area and shotcrete methods used. The performance of the Sigunit® L-50 AF also significantly depends upon the w/c ratio of the basic concrete mix, in the wet spray process, and the amount of water added during spraying, in the dry spray process.

**Application**

A typical concrete mix to be sprayed contains:

- Sika® Stabilizer
- SikaTard® set control admixtures
- Sika® Viscocrete® superplasticizer admixtures
- Sikacrete® silica fume or SikaTell® colloidal silica suspension
- Sika® FerroGard® corrosion inhibiting admixtures

Concrete temperatures should not be lower than 15°C (59°F) (especially in cases of thick shotcrete layers). Lower temperatures will require higher dosages.



<b>Clean up</b>	Rebound and other shotcrete waste accelerated with Sika® Sigunit® L-50 AF can be disposed of in the same way as non-accelerated shotcrete waste. Neat accelerator must be disposed of as special waste according to local regulations.
<b>Limitation</b>	<ul style="list-style-type: none"><li>■ The conveyance hose for the accelerator must be thoroughly cleaned before using Sika® Sigunit® L-50 AF.</li><li>■ Metal parts of the dosage equipment and/or pump coming into direct contact with Sika® Sigunit® L-50 AF must be of stainless steel.</li><li>■ The use of Sika® Sigunit® L-50 AF requires skilled and technically correct installation of dosing and conveying equipment. Please consult your Sika Canada Technical Sales Representative for further information</li></ul>
<b>Health and Safety Information</b>	<p>For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the <b>most recent Material Safety Data Sheet</b> containing physical, ecological, toxicological and other safety-related data.</p> <p>KEEP OUT OF REACH OF CHILDREN FOR INDUSTRIAL USE ONLY</p>

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelf life. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed in the Internet under [www.sika.ca](http://www.sika.ca).



**Sika Canada Inc.**  
**Head Office**  
601 Delmar Avenue  
Pointe-Claire, Quebec  
H9R 4A9

Other locations  
**Toronto**  
**Edmonton**  
**Vancouver**

**1-800-933-SIKA**  
**[www.sika.ca](http://www.sika.ca)**

An ISO 9001 certified company  
Pointe-Claire: ISO 14001 certified EMS