



PRODUCT DATA SHEET

Edition 12.2017/v1
CSC Master Format™ 03 64 23
EPOXY INJECTION GROUTING

Sikadur®-52

SUPER-LOW VISCOSITY INJECTION RESIN

| | |
|---------------------|--|
| Description | Sikadur®-52 injection resin is a solvent-free, two-component, moisture-insensitive, epoxy resin system. It is a multipurpose, high-strength adhesive formulated specifically for grouting both dry and damp cracks either by gravity feed or pressure injection. |
| Where to Use | <ul style="list-style-type: none"> ▪ To grout cracks. ▪ For pressure injection grouting. ▪ To seal slabs. |
| Advantages | <ul style="list-style-type: none"> ▪ Convenient easy mix ratio A:B = 2:1 by volume. ▪ Super-low viscosity. ▪ Unique, high strength adhesive for “can’t dry” cracks. ▪ Meets ASTM C881, Type I, II, Grade 1, Class B and C. ▪ Ministry of Transport Québec acceptance. |

Technical Data

| | |
|--|---|
| Packaging | 9 L (2.38 US gal.) unit - [Component A : 6 L (1.58 US gal.) and Component B : 3 L (0.79 US gal.)] 450 mL (15.2 US fl. oz) Pre-Pack cartridge, 12/case 200 L drums (on demand) |
| Colour | Clear, amber |
| Shelf Life | 2 years in original, unopened packaging. Store dry between 5 and 32 °C (41 and 89 °F). Condition product at 18 and 29 °C (65 and 84 °F) before using. |
| Mix Ratio | A:B = 2:1 by volume |
| Properties at 23 °C (73 °F) and 50 % R.H. | |
| Viscosity | 200 - 350 cps |
| Pot Life (250 g) | 20 - 25 min |
| Tack-Free Time | 3 - 4 hrs |
| Final Cure ASTM D695 (75% ultimate strength) | 2 days |
| Compressive Strength ASTM D695 28 days | 61 MPa (8847 psi) |
| Modulus of Elasticity ASTM D695 28 days | 1.8 GPa (2.6 x 10 ⁵ psi) |
| Tensile Strength ASTM D638 14 days | 37 MPa (5366 psi) |
| Tensile Elongation ASTM D638 14 days | 3.8% |
| Shear Strength ASTM D732 14 days | 30 MPa (4351 psi) |
| VOC Content | 0 g/L |

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

HOW TO USE

| | |
|----------------------------|---|
| Surface Preparation | Concrete surface must be clean and sound. Cracks may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, waxes, impregnations, foreign particles, and disintegrated materials. |
| Mixing | Premix each component before proportioning. To mix, proportion 1 part B and 2 parts A by volume into a clean pail. Mix thoroughly for three (3) minutes with paddle on low-speed drill (300 - 450 rpm). Mix only that quantity can be used within its pot life. |

| | |
|--------------------------------------|---|
| Application | <p>To gravity feed cracks: Pour neat Sikadur®-52 into “V” notched crack. Continue placement until completely filled. Seal underside of slab prior to filling if cracks reflect.</p> <p>For pressure injection cracks: Set appropriate injection ports based on system used. Seal entry port area with Sika AnchorFix®-2001/3001 or Sikadur®-31 Hi-Mod Gel^{CA}. When epoxy adhesive seal has cured, inject Sikadur®-52 using automated equipment or manual method. Maintain slow, steady pressure during injection.</p> <p>To seal slabs: Spread neat Sikadur®-52 over slab with flat-rubber squeegee or roller. Allow time to penetrate. Squeegee off excess while still liquid. Seal interior slabs and above grade exterior slabs only.</p> |
| Curing | Substrate temperature should not be below 4 °C (39 °F). Lower temperature will prolong cure time. |
| Clean Up | Collect with absorbent material. Dispose of in accordance with local disposal regulations. Uncured product can be removed with Sika® Epoxy Cleaner. Cured product can only be removed mechanically. |
| Limitations | <ul style="list-style-type: none"> ▪ Do not thin Sikadur®-52: Solvents may prevent proper cure. ▪ Product is a vapour barrier after cure. ▪ Do not inject cracks under hydrostatic pressure. ▪ Do not inject cracks greater than 6 mm (1/4 in) wide. |
| Health and Safety Information | <p>For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.</p> <p>KEEP OUT OF REACH OF CHILDREN FOR INDUSTRIAL USE ONLY</p> |

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SIKA CANADA INC.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9

Other locations
Toronto
Edmonton
Vancouver

1-800-933-SIKA
www.sika.ca

Certified ISO 9001 (CERT-0102780)
Certified ISO 14001 (CERT-0102791)

