



PRODUCT DATA SHEET

Edition 09.2020/v1
CSC Master Format™ 03 01 00
MAINTENANCE OF CONCRETE

SikaQuick®-1000

RAPID-HARDENING REPAIR MORTAR WITH EXTENDED WORKING TIME

Description	SikaQuick®-1000 is a one-component, rapid-hardening, early-strength gaining, cementitious, patching material for concrete.
Where to Use	<ul style="list-style-type: none"> Use on grade, above and below grade on concrete. Highway overlays and repairs. Structural repair material for concrete roadways, parking structures, bridges, dams and ramps. Full depth patching repairs. Horizontal repairs of concrete and mortar.
Advantages	<ul style="list-style-type: none"> Specifically suited for hot weather applications when extended working time is required. Rapid hardening as defined by ASTM C928. Can be used with Sikacem® Accelerator for cold conditions, increased early strengths and reduced curing time. Compatible with Sikafloor®, SikaBond®, and Sika® AcouBond systems. Allows application of an epoxy coating within 6 hours. Freeze/thaw resistant. Easy to use; economical patching and labour saving material. Contains no added chlorides. Formulated with inert, non-reactive aggregates to eliminate potential Alkali-Aggregate Reactivity (AAR). Open to foot traffic in 4 hours, to vehicle traffic in 6 hours [23 °C (73 °F)]. Easily applied to clean, sound substrates. Not a vapour barrier. Product recognized by the British Columbia Ministry of Transportation(BC MoT). Meets the requirements of CFIA and USDA for use in food plants.

Technical Data

Packaging	25 kg (55 lb) bag				
Colour	Concrete Grey				
Yield	Approx. 13 L (0.459 ft³). When extended with 11 kg (24 lb) of 10 mm (3/8 in) aggregate, yield is approx. 17 L (0.6 ft³).				
Shelf Life	12 months in original, unopened packaging. Store dry, ensuring that product is not exposed to rain, condensation or high humidity. For best results, condition product at temperatures between 18 and 29 °C (65 and 84 °F) before using.				
Mix Ratio	2.6 - 2.87 L (0.7 - 0.75 US gal.) of water per bag				
Properties at 23 °C (73 °F) and 50 % R.H.					
Working Time	Approx. 30 min after adding powder to the water				
Setting Time ASTM C266					
Initial set	Approx. 45 - 65 min				
Final set	Approx. 55 - 100 min				
Compressive Strength, Mortar ASTM C109, MPa (psi)					
1 day	30 (4350)				
7 days	40 (5800)				
28 days	50 (7250)				
*Compressive Strength ASTM C109, MPa (psi) (tested with Sikacem® Accelerator)					
Temperature	Dosage	12 hours	1 day	2 days	28 days
-5 °C	1 bottle (150 mL)	15 (2175)	19 (2755)	26 (3770)	-
-5 °C	2 bottles (300 mL)	17 (2465)	19 (2755)	27 (3916)	-
0 °C	1 bottle (150 mL)	23 (3335)	35 (5076)	41 (5946)	62 (8992)
0 °C	2 bottles (300 mL)	29 (4206)	43 (6236)	48 (6961)	69 (10 007)
10 °C	1 bottle (150 mL)	30 (4350)	40 (5800)	45 (6526)	68 (9862)
10 °C	2 bottles (300 mL)	36 (5221)	45 (6526)	50 (7250)	70 (10 152)
23 °C	1 bottle (150 mL)	42 (6091)	48 (6961)	52 (7541)	68 (9862)
23 °C	2 bottles (300 mL)	48 (6961)	53 (7687)	54 (7832)	70 (10 152)
*All moulds, mixing tools and powder components were pre-conditioned to the test temperatures. Prepared test specimens were cast and then cured at the indicated test temperatures until the time of testing.					
Liquid/solids ratio (water + Sikacem® Accelerator/SikaQuick®-1000) = 0.115; [2.87 L (0.75 US gal.) of liquid per 25 kg (55 lb) bag of SikaQuick®-1000].					
Flexural Strength ASTM C78					
28 days		8.0 MPa (1160 psi)			
Splitting Tensile Strength ASTM C496					
28 days		6.0 MPa (870 psi)			
Bond Strength ASTM C882 (modified)					
28 days		15.5 MPa (2250 psi)			
Direct Tensile Bond ACI 503					
28 days		> 2 MPa (290 psi) (substrate failure)			

Drying Shrinkage ASTM C596	
28 days	0.07 %
Modulus of Elasticity ASTM C469	
28 days	32.7 GPa (4.7 x 10 ⁶ psi)
Freeze/Thaw Resistance ASTM C666	
300 cycles	98 %
Scaling Resistance ASTM C672	
50 cycles	0.39 kg/m ² (0.08 lb/ft ²)
<i>Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.</i>	

HOW TO USE

Surface

Surface must be clean and sound. Remove all deteriorated concrete, dirt, oil, grease and other bond-inhibiting materials from the area to be repaired. Be sure repair area is not less than 6 mm (1/4 in) in depth. Preparation work should be done by appropriate mechanical means. Obtain an exposed aggregate surface with a minimum surface profile of ± 3 mm (1/8 in) (CSP 6 - 10 as per ICRI) on clean sound concrete. To ensure optimum repair results, the effectiveness of cleaning and preparation should be assessed by a pull-off test. Saw-cutting the edges is recommended. Saturate the surface to be repaired with clean water. Substrate should be saturated surface dry (SSD) with no standing water prior to application. **Reinforcing steel:** To protect it, prime reinforcing steel with SikaTop® Armatec-110 EpoCem®, applied as an anti-corrosion coating, and allow to cure.

Priming

Prime the prepared substrate with a scrub coat of SikaQuick®-1000 prior to placement of the mortar. The repair mortar has to be applied onto the wet scrub coat before it dries.

Mixing

Mechanically mix in an appropriately sized mortar mixer. Wet down all tools and mixer to be used. Start with 2.6 L (0.7 US gal.) of water added to the mixing vessel. Add one bag of SikaQuick®-1000 while continuing to mix. Add up to another 270 mL (9.0 US fl. oz) of additional water to achieve desired consistency. For application greater than 25 mm (1 in) in depth, add 11 kg (24 lb) of 10 mm (3/8 in) coarse aggregate. The aggregate must be non-reactive (as per ASTM C1260, C227, and C289), clean, well graded, saturated surface dry, have low absorption, high density and comply with ASTM C33, size number 8 per table 2.

Note: Do not overwater the mix. This may cause excessive bleeding and retardation and will reduce the strength and performance of the material.

Application

The prepared mortar must be scrubbed into substrate. Be sure to fill all pores and voids. Force the material against the edge of the repair working towards the centre. After filling the repair, screed off excess. Allow concrete to set to desired stiffness, then finish the surface. If a smoother finish is desired, use a magnesium float. Mixing, placing and finishing should not exceed 30 minutes maximum. To control setting times, cold water should be used in hot weather and hot water in cold weather.

Curing

Protect newly applied material from rain for at least 4 hours. To prevent from freezing, cover with insulating material. If necessary, cure using Sika® Florseal® WB-18 & -25, which meets ASTM C309 requirements. **Note:** Do not moist/wet cure.

Clean Up

Clean all tools and equipment immediately after use with water. Once hardened, material can only be removed manually or mechanically. Wash soiled hands and skin thoroughly in hot soapy water or use Sika® Hand Cleaner towels.

Limitations

- Important: protect stored material from exposure to rain, condensation and high humidity as moisture may penetrate packaging, causing lumps.
- For best results, condition product to 18 to 29 °C (65 to 84 °F) prior to mixing and installation. Lower temperatures may result in slower strength development and longer cure times.
- Minimum ambient and surface temperatures: 7 °C (44 °F) and rising.
- Minimum application thickness: 6 mm (1/4 in) when used neat and 25 mm (1 in) when extended with aggregates.
- Maximum application thickness: 25 mm (1 in) when used neat and 150 mm (6 in) when extended with aggregates.
- Not compatible with normal-setting bonding agents, e.g. SikaTop® Armatec-110 EpoCem® and Sikadur®-32 Hi-Mod.
- Do not featheredge.
- Use only potable water.
- Extending with aggregates will reduce compressive and flexural strengths. Dimensions and grading of aggregates will influence effect on physical properties; pre-testing is recommended.
- As with all cement based materials, avoid contact with aluminum to prevent adverse reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur®-32 Hi-Mod.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SIKA CANADA INC.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9

Other locations
Toronto
Edmonton
Vancouver

1-800-933-SIKA
www.sika.ca

Certified ISO 9001 (CERT-0102780)
Certified ISO 14001 (CERT-0102791)