



**PRODUCT DATA SHEET**

Edition 10.2020/v1  
CSC Master Format™ 03 01 00  
MAINTENANCE OF CONCRETE

# SikaTop®-123 FL

POLYMER-MODIFIED, FIBRE-REINFORCED, LIGHT COLOURED, NON-SAG, CEMENTITIOUS MORTAR CONTAINING SILICA FUME PLUS MIGRATING CORROSION INHIBITOR

<b>Description</b>	SikaTop®-123 FL is a high performance, polymer-modified, two-component, fast-setting, fibre-reinforced, non sag cementitious mortar which has a colour similar to concrete's. It is designed especially for repair of horizontal, vertical and overhead surfaces and offers the additional benefit of Sika FerroGard®-901, a migrating corrosion inhibitor.
<b>Where to Use</b>	<ul style="list-style-type: none"> <li>On grade, above, and below grade on concrete and mortar.</li> <li>For structural concrete repairs on horizontal, vertical and overhead surfaces.</li> <li>For building facades, balconies, soffits, parking structures, industrial plants, walkways, bridges, tunnels, dams and ramps.</li> </ul>
<b>Advantages</b>	<ul style="list-style-type: none"> <li>Light coloured</li> <li>Fibre-reinforced</li> <li>Improved resistance to compression and flexion</li> <li>High compressive and flexural strengths.</li> <li>Bond strength ensures superior adhesion.</li> <li>Enhanced with Sika FerroGard®-901, a migrating corrosion inhibitor</li> <li>Excellent freeze/thaw and salt scaling resistance.</li> <li>Formulated with inert, non-reactive aggregates to eliminate potential Alkali-Aggregate Reactivity (AAR).</li> <li>Ongoing testing - Alberta Transportation (AT B391) specification for patching materials.</li> <li>Ongoing testing - by the Ontario Ministry of Transportation and is qualified by The Road Authority (TRA).</li> <li>Ongoing testing- by the Ministère des Transports du Québec (MTQ).</li> </ul>

**Technical Data**

<b>Packaging</b>	20.5 kg (45 lb) unit - (A) 3.5 L jug + (B) 17 kg bag
<b>Colour</b>	Concrete colour when mixed
<b>Yield</b>	Approx. 9.3 L (0.328 ft³)
<b>Shelf Life</b>	Component A : 24 months in original, unopened packaging. Component B : 12 months in original, unopened bag. Store dry between 5 and 32 °C (41 and 89 °F). For best results, condition product between 15 and 24 °C (59 and 75 °F) before using. Protect Component A from freezing. If frozen, discard. A:B - See "Mixing" Section
<b>Mix Ratio</b>	A:B - See "Mixing" Section

**Properties at 23 °C (73 °F) and 50 % R.H.**

<b>Application Time</b>	Approx. 20 min after mixing the mortar
<b>Initial Set Time ASTM C266</b>	Approx. 60 min
<b>Final Set Time ASTM C266</b>	Approx. 110 min
<b>Density ASTM C185</b>	2210 kg/m³ (138 lb/ft³)

**Compressive Strength ASTM C109, MPa (psi)**

24 hours	25 (3625)
7 days	40 (5800)
28 days	53 (7687)

**\*Compressive Strength ASTM C109, MPa (psi) (tested with Sikacem® Accelerator)**

Temperature	Dosage	24 hours	2 days	3 days	28 days
10 °C (50 °F)	1 bottle (150 mL)	~ 2.3 (333)	~ 17 (2465)	~ 35 (5076)	~ 53 (7687)
10 °C (50 °F)	2 bottles (300 mL)	~ 10 (1450)	~ 27 (3916)	~ 36 (5221)	~ 48 (6961)
23 °C (73 °F)	1 bottle (150 mL)	~ 29 (4206)	~ 38 (5511)	~ 41 (5946)	~ 55 (7977)
23 °C (73 °F)	2 bottles (300 mL)	~ 30 (4351)	~ 35 (5076)	~ 37 (5366)	~ 57 (8267)

\*All moulds, mixing tools and powder components were pre-conditioned to the test temperatures. Prepared test specimens were cast and then cured at the indicated test temperatures until the time of testing.  
Sikacem® Accelerator added to SikaTop® "A" component jug and shaken vigorously to incorporate prior to mixing with SikaTop® "B" component.  
When using Sikacem Accelerator, reduce the quantity of Component A by the amount of Sikacem Accelerator (150 or 300 mL) to be added during mixing to ensure proper mix ratio is used.

<b>Modulus of Elasticity ASTM C469</b>	
7 days	17.2 GPa (2.5 x 10 <sup>6</sup> psi)
28 days	22.7 GPa (3.3 x 10 <sup>6</sup> psi)
<b>Tensile Splitting Strength ASTM C496</b>	
21 days	9,6 MPa (1305 psi)
<b>Flexural Strength ASTM C293</b>	
7 days	9,2 MPa (1305 psi)
28 days	11,8 MPa (1595 psi)
<b>Bond Strength CAN A23.2-6B</b>	
28 days	3 MPa (435 psi)
<b>Rapid Chloride Permeability ASTM C1202</b>	
28 days	Very low - between 100 and 1000 Coulombs
<b>Freeze/Thaw Durability Test ASTM C666</b>	
	> 90 % after 300 cycles
<b>VOC Content</b>	
	< 0.5 g/L
<b>Chemical Resistance</b>	
	Contact Sika Canada
<i>Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.</i>	

## HOW TO USE

### Surface

#### Preparation

Following ICRI Guideline 310.2, the concrete surface must be clean, sound and mechanically prepared to obtain a surface profile of CSP 5 – 6 (ex : hydrodemolition, scarification, scabbling + sandblasting, etc.). Follow ICRI Guideline 310.1 for the preparation of the repair perimeter, the repair area geometry and for the cleaning of the concrete and reinforcing steel surfaces. Verify the absence of micro cracking following ICRI Guideline 310.2.

#### Mixing

Mix using a heavy duty low speed electric drill/mixer (300 - 450 rpm) and mixing paddle (*Jiffy* or *Exomixer*®/spiral type) or a mortar mixer. Shake Component A before using, then pour approximately 80 % of Component A in a clean mixer or pail. Add slowly Component B while continuing to mix until a uniform consistency is obtained (approx : three (3) minutes). If a wetter consistency is required, add additional A Component and continue mixing until a homogenous consistency is achieved. For a smaller quantity, make sure that each component is properly premixed and that the correct ratio is used. **When using Sikacem Accelerator, reduce the quantity of Component A by the amount of Sikacem Accelerator (150 or 300 mL) to be added during mixing to ensure proper mix ratio is used.**

#### Application

At time of application, the surface should be damp but saturated surface dry (SSD) with no glistening water. A thin layer of mortar of +/- 3 mm (1/8 in) must be scrubbed firmly into substrate to fill all pores and voids. Alternatively, SikaTop® Armatec-110 EpoCem® can be used as a bonding agent. Apply the desired mortar layer before bond coat dries. Force product against the edges of repair, working toward center. After filling the repair, consolidate then trim the surface flush with adjacent concrete sides. Allow mortar to reach initial set [30-60 min after placing at 23 °C (73 °F)], then finish with wood or sponge float for a textured surface. For a smooth finish, use a steel trowel wiped with Component A during finishing. If the repair requires several lifts (layers), apply the mortar leaving a rough profile and score the surface immediately in a crosshatch pattern using the corner of a steel trowel to a depth of approximately 6 mm (1/4 in) to provide a mechanical key (with exception to the last layer). Unfinished work from previous day must be roughened and any polymer film removed to ensure bond.

#### Curing

As per ACI 308 recommendations for cement concrete, curing is required. To achieve performance consistent with Technical Data, curing must be provided by recognized curing methods, such as wet burlap covered with white polyethylene film or approved water-based curing compound, such as Sika® Florseal WB-18 & -25. Alternatively, the use of Sika® Ultracure DOT™ or NCF™ wet curing blankets is strongly recommended. Curing must commence immediately after placing and finishing. Moist or wet curing must be maintained for the first 24 hours only. Protect freshly applied mortar from direct sunlight, wind, rain and frost.

#### Clean Up

Clean all tools and equipment after use with water. Once hardened, the product can only be removed mechanically. Wash soiled hands and skin thoroughly in hot soapy water or use Sika® Hand Cleaner towels.

#### Limitations

- Minimum application thickness: 3 mm (1/8 in).
- Maximum layer thickness (vertical and horizontal) : 50 mm (2 in).
- Maximum layer thickness (overhead) : 38 mm (1½ in).
- Minimum ambient and substrate temperature: 7 °C (45 °F) and rising at time of application, unless using Sikacem® Accelerator (refer to Technical Data section for dosage recommendations and strength values at various temperatures).
- Protect the freshly applied mortar from freezing for a period of 24 hours.
- Storage is particularly important, it is essential to protect bagged material from exposure to rain, condensation and high humidity as moisture may penetrate the bag, causing lumps.
- Do not use/add water to this product.

#### Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

**KEEP OUT OF REACH OF CHILDREN  
FOR INDUSTRIAL USE ONLY**

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: [www.sika.ca](http://www.sika.ca)

**SIKA CANADA INC.**  
Head Office  
601, avenue Delmar  
Pointe-Claire, Quebec  
H9R 4A9

**Other locations**  
Toronto  
Edmonton  
Vancouver

**1-800-933-SIKA**  
[www.sika.ca](http://www.sika.ca)

Certified ISO 9001 (CERT-0102780)  
Certified ISO 14001 (CERT-0102791)

