



PRODUCT DATA SHEET

Edition 03.2018/v1
CSC Master Format™ 07 19 16
SILANE WATER REPELLENTS

Sikagard® SN-100

WATER-REPELLING SEALER

Description	Sikagard® SN-100 is an advanced generation of highly penetrating, clear, monomeric silane sealer. Using proven technology, the material has been formulated to be VOC compliant while providing an integral barrier against the ingress of moisture and water-borne salts into concrete and masonry.
Where to Use	<ul style="list-style-type: none"> ▪ Civil engineering structures. ▪ Suitable for use on exposed horizontal and vertical surfaces including bridges and parking decks, barriers, abutment walls and marine structures. ▪ To prevent the deterioration arising out of soluble salts and freeze/thaw cycles damages in reinforced concrete and porous block or brickwork. ▪ To help prolonging the design or service life of buildings and civil engineering structures.
Advantages	<ul style="list-style-type: none"> ▪ Easy to apply for an economical application. ▪ Deep penetration protects it from weathering, ultraviolet rays and abrasion. ▪ Reduces water absorption for better protection in splash zones and against driving rain. ▪ Reduces chloride ion intrusion and its negative effects through repelling of water. ▪ Can be part of corrosion management program to expand service life for reinforced concrete. ▪ Not a vapour barrier allowing treated surfaces to “breathe”. ▪ Lasts for many years; providing a long-term, cost effective solution. ▪ Ministry of Transport Québec acceptance. ▪ Approved by Alberta Transportation as a Type 1c concrete sealer for use on new bridges and overlays. ▪ VOC compliant; satisfying Environment Canada regulations. ▪ Product recognized by the British Columbia Ministry of Transportation(BC MoT).
Technical Data	
Packaging	18.9 L (5 US gal.) unit and 205 L (54.2 US gal.) drum
Colour	Clear
Yield	4.9 m ² /L (200 ft ² /US gal.) to 8.8 m ² /L (360 ft ² /US gal.) depending on the substrate
Shelf Life	<p>Alberta Transportation Specification: Type 1c: 158 mL/m² [equivalent to 6.33 m²/L (257 ft²/US gal.)]</p> <p>2 years in original, unopened packaging. Store between -18 and 30 °C (0 and 86 °F). Condition material between 10 and 30 °C (50 and 86 °F) prior to use.</p>
Properties at 25 °C (77 °F) and 50 % R.H.	
Active Ingredients	100 %
Density	0.88 kg/L (7.3 lb/US gal.)
Viscosity	5 - 10 cps
Curing	The reaction of the residual silane monomer with the substrate will take at least 24 hours at a temperature of 25 °C (77 °F). Cure time is considerably longer at colder temperatures.
VOC Content	333 g/L
Chemical Resistance	Consult Sika Canada
<i>Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.</i>	

HOW TO USE

Surface Preparation

All surfaces must be clean, sound, frost free and dry (maximum depth of penetration is achieved when substrates are dry, with no damp patches). Any existing coatings, surfaces treatments, accumulated pollutants, dust, dirt, oil and efflorescence must be removed. A substrate clogged with dirt or oil will not permit proper sealer penetration. Usually no preparation is required for uncoated building envelopes. Uncoated surfaces must be free from curing compound residues and any material or contaminants detrimental to penetration. Best results are achieved when Sikagard® SN-100 is applied onto 28 day old or older concrete, however, due to its high alkali resistance, it is possible to apply it earlier, consult Sika Canada for more information.

All substrates requiring preparation, such as contaminated surfaces or horizontal concrete slabs, must be properly cleaned before the sealer is applied. This is best achieved using light sand-blasting, shot-blasting or high pressure water blasting. Allow adequate time for surfaces to dry (for best penetration) before proceeding with application.

Mixing	Stir material to ensure the material is fully blended and of uniform consistency using a slow-speed (300 - 450 rpm) drill fitted with a <i>Jiffy</i> -style paddle.
Application	<p>Vertical Surfaces: Apply Sikagard® SN-100 using a brush, roller or low pressure spray (<i>Chapin Viton™</i> or similar), working from top to bottom by maintaining a 30 cm (12 in) curtain (run down). When applying the material on a vertical surface, avoid accumulation and run-off of the material. In the event of material accumulation or run-off lines being formed, redistribute the material on the surface or remove by sponging. In most cases, the flood coat should be applied in two (2) passes, “wet on wet” with the second pass at right angles to the first. Material coverage should not be greater than 4.9 m²/L total (200 ft²/US gal.) in order to achieve the desired effect.</p> <p>Horizontal Surfaces: Apply Sikagard® SN-100 using a roller or low pressure spray (<i>Chapin Viton™</i> or similar), ensuring that product penetrates the substrate and does not “pond” or “puddle” on the surface. If ponding occurs, make sure to redistribute or remove the excess material on the surface before material starts to dry and form a film that will prevent penetration of excess material. Material coverage should not be greater than 4.9 m²/L (200 ft²/US gal.) in order to achieve the desired effect. Where working on a horizontal surface the flood coat should be applied in two (2) passes, “wet on wet” with the second pass at right angles to the first.</p> <p>Complete and correct coverage of surfaces is crucial to the success of such sealers</p>
Clean Up	Uncured material can be removed using Sika® Epoxy Cleaner or mineral spirits. Cured product can only be removed mechanically. Wash soiled hands and skin thoroughly in hot soapy water or use Sika® Hand Cleaner towels.
Limitations	<ul style="list-style-type: none"> ▪ Sikagard® SN-100 is best applied onto 28 day old concrete or older, however, due to its high alkali resistance it is possible to apply it earlier, though lower penetration might be expected. Contact Sika Canada for more detailed information. ▪ Can be applied at temperatures down to -10 °C (14 °F), providing the surface is ice-free/frost-free, though lower penetration might be expected. ▪ Not recommended for exterior applications if rain is expected within 12 hours. ▪ Not intended for waterproofing under hydrostatic pressure, in permanent contact with water or for below ground waterproofing. ▪ Not intended to seal visible cracks from moisture ingress. ▪ Building materials not to be treated (e.g. window frames and glazing) must be protected from contact. In case of splashes, clean immediately using clean water and a squeegee. ▪ Some coatings and bituminous materials may be damaged by the Sikagard® SN-100; care is required during application or protection against contact may be necessary. ▪ Surfaces treated with Sikagard® SN-100 cannot be overcoated with either cement or lime-wash based paints. ▪ Sikagard® SN-100 is clear and typically “invisible” to the eye once cured and dried, however if there are strict aesthetic requirements (for example on natural stone) it is recommended to undertake preliminary trials as slight darkening of some surfaces may occur. ▪ Do not let dry excess material, darkening, change of colour or appearance of substrate may occur.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SIKA CANADA INC.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9

Other locations
Toronto
Edmonton
Vancouver

1-800-933-SIKA
www.sika.ca

Certified ISO 9001 (CERT-0102780)
Certified ISO 14001 (CERT-0102791)

