

SikaFast®-555 L05 – Comparative Chart

Fast curing, 2-component structural adhesive

BUILDING TRUST
CONSTRUIRE LA CONFIANCE



	SikaFast®-555 L05	SikaFast®-5215 NT
Technology	2C Structural Adhesive	2C Structural Adhesive
Open Time (@ 23 °C / 50 % r.h.)	5 minutes	5 minutes
Fixing Time (@ 23 °C / 50 % r.h.)	15 minutes	15 minutes
Application Temperature	5-40 °C	5-40 °C
Elongation at Break	200 %	200 %
Tensile Strength	11 MPa	10 Mpa
Lap-Shear Strength	12 MPa	10 Mpa
Shore D Hardness	50	50
E-Modulus	200 MPa	250 MPa
Glass Transition Temperature	55 °C	60 °C
Packaging	50 mL Cartridges	50 mL Cartridges
Product Reference Code	571661	74307