



.....

SAKRETE ASPHALT REPAIR

.....

SAKRETE Asphalt Repair is a pre-blended, ready-to-use, cold patch, pot hole repair mixture made of blended asphalts, aggregates and selective additives specifically designed for repairing black-top surfaces. The asphalt is designed to be poured from the bag into the hole and compacted.

FEATURES & BENEFITS

- Pour directly from the bag
- Easily compacted
- Premium quality

USES

Ideal for repairing black-top surfaces 2.5 cm (1") to 10 cm (4") thick, up to an area of 0.4 m² (4 ft²). Repair asphalt drives, walks and parking areas that have sunk, wide cracks, pot holes or areas damaged from gas and oil. Not recommended for use on curbs, speed bumps and ramps, or for new driveway extensions.

PROCEDURES

In cold weather, keep bag in a warm place for at least 24 hours before using.

Surface Preparation: Chisel out and remove all existing, damaged asphalt, to a depth of 5 cm (2") to 10 cm (4"). Square up the area to be repaired, ensuring that all the sides are vertical. Avoid a bird bath shaped edge. Using a stiff broom or brush, remove all loose particles, mud, dust, grass, etc. Remove any unsound portions of the base. Fill deeper holes with gravel to proper depth.

Placing: Pour SAKRETE Asphalt Repair into hole and level about 1.3 cm (1/2") higher than surrounding pavement. Thoroughly compact using a hand-tamper. Deep holes should be compacted in layers 5 cm (2") thick or less. Final repair should not exceed 10 cm (4") in depth.

NOTE: The greater the compaction, the better the patch.

CURING

Repair may normally be used after 3-7 days. However, hardening is prolonged in warm weather.

SEALING

Allow 60-90 days curing time before applying a driveway sealer, and follow driveway sealer manufacturer directions.

CLEAN UP

Clean tools with mineral spirits immediately after use.

YIELD

30 KG (66 lb) yields approximately 0.2 m² (2 ft²) at 7.6 cm (3") thick. Coverage indicated varies with the irregularity of the surface and the level of compaction.

PACKAGING

30 KG (66 lb) plastic bag

UPC

055226160663

STORAGE & SHELF LIFE

Compaction from storage does not change the workability. Material should be stored in a dry, covered area, protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

Do not swallow. Do not get in eyes. Do not get on skin or clothing. Do not breathe fumes. Handle with care. Keep out of reach of children. Wear safety glasses and protective clothing. Use only in a well-ventilated area.

FIRST AID TREATMENT: If swallowed call a poison control center or doctor immediately.

WEBSITE

For more information and other projects, visit us at www.sakretecanada.com or call us at 866-725-7383.



.....
SAKRETE ASPHALT REPAIR
.....

Warranty: This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade. [REV.0005_07/18/19]

KING PACKAGED MATERIALS COMPANY
.....

Oakville Office
555 Michigan Dr.,
Oakville, ON
L6L 0G4

Montreal Office
3825 rue Alfred-Laliberté,
Boisbriand, QC
J7H 1P7

Brantford Office
541 Oak Park Rd.,
Brantford, ON
N3T 5L8

Sudbury Office
644 Simmons Rd.,
Dowling, ON
P0M 1R0