



PRODUCT DATA SHEET

SikaSeal®-330

Heat curing seam sealant for high temperature powder coat applications

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base		Acrylic Plastisol
Colour (CQP001-1)		White
Density		1.41 kg/l
Application temperature	ambient	5 – 30 °C
Non-sag properties		Good
Curing conditions	standard	25 minutes at 200 °C ^A
Shore A hardness (CQP023-1 / ISO 48-4)		60
Tensile strength (ASTM D412)		3 MPa
Elongation at break (ASTM D412)		250 %
Service temperature (CQP513-1)		-25 – 90 °C
Shelf life		9 months ^B

CQP = Corporate Quality Procedure

^{A)} substrate temperature

^{B)} 23 °C / 50 % r. h.

DESCRIPTION

SikaSeal®-330 is a 1-component, cold-applied heat-curing sealant based on acrylic plastisols. It is a flexible sealant especially designed for sealing metals prior to a powder-coating process.

PRODUCT BENEFITS

- Capable of withstanding baking / curing temperatures up to 230 °C
- Superior compatibility with many powder coats and powder coating processes
- Bonds well to wide variety of substrates
- Very good application and tooling characteristics

AREAS OF APPLICATION

SikaSeal®-330 is suitable for seam sealing of truck bodies, cabs, and other manufacturing units and cures in the subsequent powder coat baking process. It is suitable for use with e-coated metals as well as treated aluminum and steel. It provides a Class A finish with a variety of powder coat chemistries. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

CURE MECHANISM

SikaSeal®-330 is cured by heat. The cure rate depends on temperature and time of exposure. The most suitable heat sources are convection ovens. The minimum bake / cure temperature is 190 °C and the maximum must not exceed 230 °C.

It is highly recommended to perform tests with original parts to ensure proper curing and function of the bonded part under original conditions.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Adhesion must be verified by tests on original substrates.

Application

SikaSeal®-330 can be processed between 5 °C and 30 °C with manual, pneumatic or electric driven piston guns as well as pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Tooling and finishing

If needed, it is best to dry tool the sealant after application without the use of any chemical tooling or finishing agents.

If a chemical tooling or finishing agents is used, it must be tested for suitability and compatibility prior to use.

Removal

Uncured SikaSeal®-330 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using a suitable industrial hand cleaner and water.

Do not use solvents on skin.

Overpainting

SikaSeal®-330 is suitable for powder coating paint processes and is compatible with very light colors. For best results, the time between powder coat application and curing must be as short as possible.

All paints have to be tested by carrying preliminary trials under manufacturing conditions.

STORAGE CONDITIONS

SikaSeal®-330 has to be kept between 5 °C and 25 °C in a dry place. Do not expose it to direct sunlight.

If SikaSeal®-330 is stored at higher temperatures the shelf life will be reduced.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

Cartridge	300 ml
-----------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

PRODUCT DATA SHEET

SikaSeal®-330

Version 01.01 (03 - 2025), en_CA
014117303300001000

Sika Canada Inc.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

