



.....
TYPE N MASONRY CEMENT & TYPE S MASONRY CEMENT
.....

Masonry Cement is prepackaged cement with ingredients to provide the plasticity required for masonry work. Masonry Cements are available as either Type N Masonry Cement or Type S Masonry Cement.

USES

Type N Masonry Mortar is recommended for general use in non-load-bearing walls, as well as in exterior veneer walls not requiring high strength.

Type S Masonry Mortar is recommended for use in all masonry below grade, as well as in exterior load-bearing walls requiring high strength.

Type N Masonry Cement or Type S Masonry Cement can also be used in parging and stucco work. DO NOT use masonry cements for concrete jobs.

PROCEDURES

Mix and substrate temperatures should be maintained between 5 °C and 30 °C (40 °F and 86 °F) for at least 24 hours prior to and 48 hours after.

Mixing: Masonry cements are mixed with sand in the following proportions (by volume).

- 1 part Type N or Type S Masonry Cement
- 3 parts damp, loose, brick sand

Mix the cement and sand. Add water until the mortar is of suitable "buttery" consistency.

PAINTING

Concrete must be fully cured (approximately 28 days) and dry before painting. Refer to paint manufacturer directions for application instructions.

YIELD

Using proportions suggested, one (1) bag of masonry cement is required to lay 35 to 40 blocks, or 135 bricks, approximately.

PACKAGING

Type N Masonry Cement 30 KG (66 lb) bag
Type S Masonry Cement 33.3 KG (66 lb) bag

STORAGE & SHELF LIFE

Material should be stored in a dry covered area protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

CAUSES BURNS. Do not swallow. Do not get in eyes. Do not get on skin or clothing. Do not breathe fumes. Handle with care. Keep out of reach of children. Wear safety glasses, protective clothing and dust mask. Use only in a well-ventilated area.

FIRST AID TREATMENT: Contains cement, when wet forms a calcium hydroxide solution. If swallowed call a poison control center or doctor immediately. Do not induce vomiting. If in eyes, rinse with water for at least 15 minutes. If on skin, rinse well with water. If on clothes remove clothes. If breathed in, move person to fresh air.

WEBSITE

For more information and other projects, visit us at www.sakretecanada.com or call us at 866-725-7383.



.....
TYPE N MASONRY CEMENT & TYPE S MASONRY CEMENT
.....

Warranty: This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade. [REV.0004_07/18/19]

KING PACKAGED MATERIALS COMPANY
.....

Oakville Office
555 Michigan Dr.,
Oakville, ON
L6L 0G4

Montreal Office
3825 rue Alfred-Laliberté,
Boisbriand, QC
J7H 1P7

Brantford Office
541 Oak Park Rd.,
Brantford, ON
N3T 5L8

Sudbury Office
644 Simmons Rd.,
Dowling, ON
P0M 1R0