



# PRODUCT DATA SHEET

## SikaTop®-122 Plus

POLYMER-MODIFIED, CEMENTITIOUS, TROWEL-GRADE MORTAR, PLUS MIGRATING CORROSION INHIBITOR



### PRODUCT DESCRIPTION

SikaTop®-122 Plus is a polymer-modified, with migrating corrosion inhibitor added, cementitious, 2-component, fast-setting, trowel-grade, easy-to-use patching mortar. Excellent for vertical and horizontal surfaces.

### WHERE TO USE

- Use on grade, above, and below grade on concrete and mortar
- Use as a topping for concrete surfaces
- Structural repair material for parking structures, industrial plants, walkways, bridges, tunnels, ramps, and dams
- Use to level concrete surfaces

### CHARACTERISTICS / ADVANTAGES

- Superior abrasion resistance over conventional cement mortar
- High bond strength ensures superior adhesion
- Compatible with thermal coefficient of expansion of concrete
- High early strength
- Good freeze/thaw resistance
- Increased resistance to de-icing salts
- Not a vapour barrier
- High compressive and flexural strengths
- Will not corrode stressed steel

- Formulated with inert, non-reactive aggregates to eliminate potential Alkali-Aggregate Reactivity (AAR)
- Not flammable
- Meets MTO MI-67 specification for concrete patching materials
- Meets Alberta Transportation (AT B391) specification for patching materials
- Complies with NSF-ANSI Standard 61 for potable water contact (available by special order only)
- Product recognized by the British Columbia Ministry of Transportation (BC MoT)
- Approved by the Ontario Ministry of Transportation (MTO)
- Approved by the Ministère des Transports du Québec (MTQ)
- Product qualified by The Road Authority (TRA)
- Meets the requirements of CFIA and USDA for use in food plants

### ENVIRONMENTAL INFORMATION

- Conformity with LEED®v4 MR Credit (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED®v4 MR Credit (Option 1): Building Product Disclosure and Optimization – Material Ingredients Reporting
- Conformity with LEED®v4 MR Credit (Option 1): Building Product Disclosure and Optimization – Sourcing of Raw Materials

### PRODUCT INFORMATION

CSC MasterFormat®

03 01 00 | MAINTENANCE OF CONCRETE

Packaging

28.5 kg (62.7 lb) unit

Product Data Sheet

SikaTop®-122 Plus

January 2023, Version 01.01

020302040070000021

Appearance / Colour	Concrete Grey when mixed	
Shelf Life	Component A : 24 months in original, unopened packaging Component B : 12 months in original, unopened bag	
Storage Conditions	Stored (unopened) in a dry place at temperatures between +5 °C and +32 °C (41°F and 89 °F). For best results, condition product between +15 °C and +24 °C (59 °F and 75 °F) before using. Protect Component A from freezing. If frozen, discard.	
Density	2 200 kg/m <sup>3</sup> (137 lb/ft <sup>3</sup> )	(ASTM C185)

## TECHNICAL INFORMATION

Compressive Strength	24 hours	~ 18 MPa (2 610 psi)	(ASTM C109)
	7 days	~ 37 MPa (5 366 psi)	
	28 days	~ 50 MPa (7 250 psi)	
Splitting Tensile Strength	~ 5.5 MPa (797 psi)		(ASTM C496) 21 days
Pull-Out Resistance	7 days	2.1 MPa (>300 psi)	(ASTM C1583) +23 °C (73 °F) / 50 % r.h.
	28 days	2.8 MPa (400 psi)	
Shrinkage	28 days	25 mm x 25 mm x 285 mm (1"x1"x11-1/4") specimen	(ASTM C157 modified (mod. ICRI 320.3R)) +23 °C (73 °F) / 50 % r.h.
		75 mm x 75 mm x 285 mm (3"x3"x11-1/4") specimen	
Ring Test	Duration	>70 days	(ASTM C1581) +23 °C (73 °F) / 50 % r.h.
	Average Max Strain	-9 µstrain	
	Average Stress Strain	0.49 psi/day	
	Potential for Cracking	Low	
Baenziger Block	90 days	No cracking	

## APPLICATION INFORMATION

Mixing Ratio	A:B = 1:7 by weight depending on consistency required		
Consumption	Neat	0.02 m³ (0.51 ft³) per unit	
	Extended with 19 kg (42 lb) of 9.5 mm (3/8 in) gravel	0.03 m³ (0.75 ft³) per unit	
	Note: Coverage figures do not include allowance for surface profile and porosity or material waste.		
Yield	Approx. 13 L (0.459 ft³)		
Layer Thickness		Min.	Max. in one lift
	Neat	3 mm (1/8 in)	25 mm (1 in)
	Extended	25 mm (1 in)	100 mm (4 in)
Product Temperature	+18 °C to +24 °C (65 °F to 75 °F)		
Ambient Air Temperature	> +7 °C (> 45 °F)		

**Substrate Temperature** > +7 °C (> 45 °F)

**Application Time** Approx. 30 min after mixing the mortar

**Finishing Time** Approx. 50 min to 75 min after placing the mortar

## BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods. Properties tested at +23 °C (73 °F) / 50 % r.h. unless stated otherwise.

## LIMITATIONS

Application Thickness:	Minimum:	Maximum:
Neat:	3 mm (1/8 in)	38 mm (1½ in)
Extended:	38 mm (1½ in)	100 mm (4 in)

- Mortar should be applied at thinner layer thicknesses, which do not result in slumping, when used vertically.
- Minimum application thickness for surfaces subject to abrasion: 6 mm (1/4 in).
- Minimum ambient and substrate temperature: +7 °C (45 °F) and rising at time of application, unless using Sikacem® Accelerator (refer to Technical Data section for dosage recommendations and strength values at various temperatures).
- Extending with aggregates will reduce compressive and flexural strengths. Dimensions and grading of aggregates will influence effect on physical properties; pre-testing is recommended where required.

## ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

Remove all deteriorated concrete, dirt, oil, grease or any contaminants or conditions that may affect adhesion or overall product performances. Following ICRI Guideline 310.2, the concrete surface must be clean, sound and mechanically prepared to obtain a surface profile of CSP 6 – 10 (ex : hydrodemolition, scarification, scabbling + sandblasting, etc.). Follow ICRI Guideline 310.1 for the preparation of the repair perimeter, the repair area geometry and for the cleaning of the concrete and reinforcing steel surfaces. Verify the absence of micro cracking following ICRI Guideline 310.2. To ensure

optimum repair results, the effectiveness of cleaning and preparation should be assessed by a pull-off test.

### MIXING

Mix mechanically using a heavy-duty, low-speed drill (300 - 450 rpm) with a Mud Mixer/Box or Propeller-type paddle. Shake Component A before using, then pour approximately 85 % of Component A into mixing container. Add Component B while continuing to mix. Mix to a uniform consistency for a maximum of three (3) minutes. Add additional Component A to mix if a wetter consistency is desired. Should smaller quantities be required, be sure that components are dosed in correct ratio and thoroughly premix component B before dosing. Ratio is A:B = 1:7 by weight approximately. For application greater than 38 mm (1½ in) in depth, add up to 17 kg (37.5 lb) of 10 mm (3/8 in) coarse aggregate. The aggregate must be non-reactive (reference ASTM C1260, C227, and C289), clean, well graded, saturated surface dry, have low absorption, high density and comply with ASTM C33, size number 8 per table 2.

### APPLICATION

At time of application, surfaces should be damp (saturated surface dry) with no glistening water films. A scrub coat should be applied prior to the placement of the mortar. Apply a 3 mm (1/8 in) thick scrub coat of SikaTop®-122 Plus into the substrate, filling all pores, voids and edges. Alternatively, SikaTop® Armatec-110 EpoCem® can be used as a bonding agent. Apply mortar before bond coat dries, then screed. Force product against edge of repair, working toward center. Allow mortar to reach initial set [50 to 75 minutes after placing at +23 °C (73 °F)], then finish with wood or sponge float. For extra smooth finish, wipe steel trowel with Component A during finishing. If repair requires several lifts, each lift must be applied as soon as the previous lift will support it and all surfaces but the last must be left rough. Unfinished work from previous day must be roughened and any polymer film removed to ensure bond.

### CURING TREATMENT

As per ACI 308 recommendations for cement concrete, curing is required. To achieve performance consistent with Technical Data, curing must be provided by recognized curing methods, such as wet burlap covered with white polyethylene film or approved water-based curing compound, such as Sika® Florseal WB-18 & -25. Alternatively, the use of Sika® Ultracure DOT™ or NCF™ wet curing blankets is strongly recommended. Curing must commence immediately after placing and finishing.

Moist-curing must be maintained for the first 24 hours only. Protect freshly applied mortar from direct sunlight, wind, rain and frost.

## **CLEAN UP**

Clean all tools and equipment after use with water. Once hardened, the product can only be removed manually or mechanically.

## **LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## **LEGAL NOTES**

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: [www.sika.ca](http://www.sika.ca)

### **Sika Canada Inc.**

Head Office  
601, avenue Delmar  
Pointe-Claire, Quebec  
H9R 4A9  
1-800-933-SIKA  
[www.sika.ca](http://www.sika.ca)

### **Other locations**

Boisbriand (Quebec)  
Brantford; Cambridge;  
Sudbury; Toronto (Ontario)  
Edmonton (Alberta)  
Surrey (British Columbia)

### **Product Data Sheet**

SikaTop®-122 Plus  
January 2023, Version 01.01  
020302040070000021

SikaTop-122Plus-en-CA-(01-2023)-1-1.pdf