BUILDING TRUST
CONSTRUIRE LA CONFIANCE

PRODUCT DATA SHEET

Sikafloor®-2540 W NA

Breathable, Water-Based Epoxy Coating For High Performance Floor Finishes

PRODUCT DESCRIPTION

Sikafloor®-2540 W NA is a two-component, breathable, water-based, low VOC, low odour, glossy finish, pigmented epoxy coating available in an unlimited colour range.

After curing, Sikafloor®-2540 W NA provides a tough, finely textured finish that will withstand light to medium-duty traffic, chemical exposure and repeated cleaning cycles.

WHERE TO USE

Sikafloor®-2540 W NA may only be used by experienced professionals.

- As a thin-film, vapour permeable pigmented coating on new and refurbished interiour concrete subsrates.
- As a breathable coating for concrete surfaces in chemical, pharmaceutical, food processing and preparation facilities, warehouses and workshops.
- As a wear resistant finish that will withstand contact with mildly corrosive chemicals and scrubbing during wash-down.
- As a top coat part of the Sikafloor® Multiflex PS 52 MRW (CA) (formally Sikafloor® Resoclad MRW Type II) & Sikafloor® Multiflex PS 53 MRW (CA) (formally Sikafloor® Resoclad MRW Type III) Mechanical Room Waterproofing Systems.

CHARACTERISTICS / ADVANTAGES

- Good resistance against mild corrosive chemicals, wear factors and scrubbing while being cleaned
- Aesthetic, glossy, fine textured finish with excellent opacity
- Unlimited colours, no minimums required
- Water-based, Low VOC, ideal for interior application without disruption to ongoing operations
- Breathable - permeable to water vapour
- Able to withstand light to medium-duty traffic (i.e., pedestrians and light handling equipment on pneumatic tires)

ENVIRONMENTAL INFORMATION

Potential of contribution towards LEED®v4 credits.
Contact Sika Canada

APPROVALS / CERTIFICATES

- Meets the requirements of CFIA for use in food plants

PRODUCT INFORMATION

Packaging	**Components A+B:** 18.9 L (5 US gal) Component A: 7.57 L (2 US gal) Component B: 11.36 L (3 US gal)

Appearance / Colour	Special colours available on request.
Shelf Life	1 year in original, unopened packaging.
Storage Conditions	Store in a dry place, protected from freezing at a temperature between 5 °C and 32 °C (41 °F and 90 °F). Protect from freezing. If Sikafloor®-2540 W NA has frozen, contact Sika Canada.
Volatile organic compound (VOC) content	~24 g/L
Viscosity	A+B: ~2000 cPs (depending upon the colour selected)
Solid content by weight	~61.5 % (+/- 5 %) - Depending upon colour
CSC MasterFormat®	**09 67 00 | FLUID-APPLIED FLOORING**

TECHNICAL INFORMATION

Shore D Hardness	~80	(ASTM D2240)
Abrasion Resistance	~0.118 g loss: CS17 wheel /1000 g /1000 cycles	(ASTM D4060)
Resistance to Impact	~0.331 joules (~0.45 ft lb)	(ASTM D2794)
Elongation at Break	~2.8 %	(ASTM D638)
Pull-Off Strength	> 2.0 MPa (> 290 psi) (concrete failure)	(ASTM D7234)
Chemical Resistance	Chemical Resistance Consult Sika Canada	
Permeability to Water Vapour	~3.9 Perm at 10 mil d.f.t.	(ASTM E96 - Procedure B)
Coefficient of Friction	~0,30 Wet (smooth)	ANSI A326.3 / BOT 3000e
Water Absorption	~6.85 % (24 hours)	(ASTM C413)

APPLICATION INFORMATION

Mixing Ratio	A:B = 2:3 by volume
Consumption	Approximately 4 m²/L to 5 m²/L (163 ft²/US gal to 203 ft²/US gal) at 8 to 10 mil w.f.t. / 4 to 5 mil d.f.t. per coat Two (2) coats recommended for optimum service. **Note:** Actual coverage rates and material consumption will depend upon porosity and profile of substrates. Allowance must also be made for variation in film thickness or number of coats required to achieve complete coverage of surfaces. Test sections are recommended to establish correct coverage.
Product Temperature	Condition product between 18 °C to 24 °C (65 °F to 75 °F) before using and during the application.
Ambient Air Temperature	Minimum: 10 °C (50 °F) / Maximum: 30 °C (86 °F) **Note:** Mixing carried out under conditions where the Sikafloor®-2540 W NA temperature and ambient temperature are below 18°C (65°F) will result in reduced product workability and slower curing rates.

Relative Air Humidity

Maximum 75 % (during application and curing).

Note: Sikafloor®-2540 W NA should not be applied when the ambient air relative humidity is > 75% as curing times will be longer and water will be retained in the film reducing ultimate coating performance. Provide adequate fresh air ventilation to remove the excess moisture from the curing product.

Dew Point

Substrate must be at least 3 °C (5 °F) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or "blushing" on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

Substrate Temperature

Minimum: 10 °C (50 °F) / Maximum: 30 °C (86 °F)

Note: Any attempt to apply Sikafloor®-2540 W NA at substrate temperature conditions less than 18 °C (65 °F) will result in an increase in viscosity and slower cure rates.

Substrate Moisture Content

Moisture content of concrete substrate must be ≤ 6 % by mass (pbw– part by weight) as measured with a Tramex® CME/CMEX type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation ICRI / CSP 2-3).

Pot Life

	10 °C (50 °F)	20 °C (68 °F)	30 °C (86 °F)
250 g (8,8 oz)	~1 hour	~30 minutes	~25 minutes

Curing Time

Substrate Temperature	Foot Traffic	Light Traffic	Normal Traffic
10 °C (50 °F)	~36 hours	~3 days	~5 days
23 °C (73 °F)	~18 hours	~36 hours	~3 days
30 °C (86 °F)	~12 hours	~30 hours	~2 days

Full Cure: ~7 days at 23 °C (73 °F)

Waiting Time / Overcoating

Temperature	Minimum	Maximum
10 °C (50 °F)	~18 hours	72 hours
23 °C (73 °F)	~10 hours	48 hours
30 °C (86 °F)	~7 hours	24 hours

IMPORTANT: If the maximum waiting time has been exceeded. The previous coat must be lightly sanded, to remove all gloss; vacuum cleaning using a brush attachment followed promptly with a solvent wipe off the surface as per the following generally accepted practices:

- **Avoid using solvent that can leave a oily residue:** (such as, but not limited to most mineral spirit).
- **Avoid Paper Towels:** Pre-treated shop towels or standard paper towels may contain silicone or manufacturing additives that will ruin your paint job. Stick to lint-free cotton cloths or dedicated microfiber towels.
- **Change Rags Frequently:** As soon as a rag becomes visibly dirty, discard it or fold it to a clean side. Continuing to wipe with a saturated, dirty rag just re-deposits contaminants onto the surface.
- **Wet Wipe:** Pour a solvent (onto the first rag. Do not dip the rag

into the solvent container; pour it directly to keep your supply clean). à

- **Lift:** Wipe down a small, manageable section (e.g., ~0.5 m^2 [~ 4-6 ft^2]) of the surface. Use enough pressure to break up and lift the oils or sanding dust. Rotate the cloth frequently so you are always using a clean spot.
- **Dry Wipe:** Before the solvent can flash off (evaporate) and dry on the surface, wipe the same section with a second, clean, lint-free rag. When used correctly, this second cloth absorbs residual solvent and removes materials that could reduce or prevent adhesion or the proper performance of the next coat.

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.
Properties tested at 23 °C (73 °F) and 50 % R.H. unless stated otherwise.

LIMITATIONS

NOTE: The user is solely responsible for the proper use of the product. Any site visit carried out by Sika® personnel, upon the user's request, is intended solely to provide written technical recommendations based on Sika® documentation. They are in no way intended to supervise, approve or control the quality of the work performed on site. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose.

- Do not apply Sikafloor® to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor® product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Do not apply to cracked or unsound substrates.
- Do not apply on porous surfaces where outgassing conditions are present during the application of Sikafloor®-2540 W NA.
- Do not apply on porous surfaces where a transfer of moisture vapour may occur during application.
- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur.
- Do not use on exterior, Sikafloor®-2540 W NA is for interior use only.
- Do not apply to surfaces where water vapour could condense and freeze.
- Do not apply to substrates exposed to extreme thermal shock.
- This product is not designed for negative side waterproofing.
- Do not dilute Sikafloor®-2540 W NA. Adding diluents (water, solvent, etc.) will slow curing and reduce the final properties of this product. Diluents must never be added to the mixture. Adding diluent will void any applicable Sika® warranty.
- May be incompatible with certain existing coatings. Consult with Sika Canada for guidance before specifying or application and carry out trial sections.
- Not recommended for use on surfaces which are exposed to highly corrosive chemicals or heavy wear.

As well, Sika recommends:

- That prior to application, measure and confirm the following: substrate moisture content, ambient relative humidity ambient and surface temperature and dew point. During installation, confirm and record above values at least once every three (3) hours, or more frequently whenever conditions change (e.g., ambient temperature rise/fall, relative humidity increase/decrease, etc.).
- To verify and ensure that moisture content of concrete substrate must be ≤ 4 % (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically-prepared surface according to this product data sheet (preparation to ICRI / CSP 3 to 4). Do not apply to concrete substrate with moisture levels exceeding 4 % (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate exceeds 4 % (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor®-1620 or Sikafloor®-81 EpoCem® CA.
- That for specific project requirements, when relative humidity measurements of the concrete substrate taken according to ASTM F2170, the values should be below 85%. However, if these values are found to be above 85% (according to ASTM F2170), Sikafloor®-1620 or Sikafloor®-81 EpoCem® CA must be used. Sikafloor®-1620 or Sikafloor®-81 EpoCem® CA must be used.
- To keep in mind that ASTM F2170 testing is not a substitute for measuring substrate moisture content with a Tramex® CME/CMExpert type concrete moisture meter as described above.

- That during the application and curing, the maximum ambient humidity should not exceed 75%.
- To beware of Dew Point condensation (the substrate temperature may be lower than the ambient temperature).
- To maintain and extend existing expansion joints through the Sikafloor® flooring system.
- That applied material will follow undulations, depressions, lines, etc. of the underlying substrate. Visual appearance of the finished surface may vary, including, but not limited to, reflection of "waviness", wall transitions, etc.
- That any aggregate used with Sikafloor®-2540 W NA must be non-reactive and oven-dried.
- To take into account that the mechanical and physical properties are achieved when full curing is complete.
- That freshly applied material should be protected from dampness, condensation and water for at least 72 hours. Protect substrate during application from condensation from pipes or any overhead leaks.
- To take in account that colour uniformity cannot be completely guaranteed from batch to batch (numbered). Take care when using Sikafloor®-2540 W NA products to draw from inventory in batch number sequence, do not mix batch numbers in a single floor area.
- To take in account that Sikafloor®-2540 W NA will discolour over time when exposed to UV light and under certain artificial lighting conditions.
- To take into account that direct-fired gas or kerosene heaters produce byproducts that can have adverse effects on the curing resin. To avoid this occurrence, heaters must be exhausted to exterior of the building to avoid defects such as surface blush, whitening, loss of adhesion or other surface deficiencies.
- To beware of airflow and changes in airflow. Introduction of dust, debris, and particles, etc., may result in surface imperfections and other defects.
- Published Dynamic Coefficient of Friction (DCOF) wet and dry test results are approximate values based on laboratory test samples produced in a controlled environment following the application instructions published on the product data sheet. Resin flooring products are hand-applied finishes subject to minor variations in surface texture due to influences partly beyond Sika Canada's control. Substrate profile, environmental conditions, variable regional aggregate size, shape and gradation, aggregate distribution, uniformity of applied resin mil thickness, and application technique can all affect the final DCOF test results achieved. Adequate provision should be made by the client throughout the selection and installation process to ensure the finished surface texture meets the end user's traction requirements.

ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

SUBSTRATE QUALITY

Concrete surfaces must be clean and sound. The compressive strength of the concrete substrate should be at least 25 MPa (3625 psi) at 28 days and a minimum of 1.5 MPa (217 psi) in tensile strength, at the time of the application.

Substrates must be free of contaminants such as dust, dirt, existing paint films, efflorescence, exudates, laitance, form, hydraulic or fuel oils, brake fluid, grease, fungi, mildew, biological residues or any other contaminants which may prohibit good bond or conditions of the substrate that may reduce the overall performances of Sikafloor®-2540 W NA.

SURFACE PREPARATION

Before work commences, examine the areas to be covered and report any improper condition(s) in writing to the general contractor, architect or engineer (or otherwise, the owner). User shall not proceed with the work until surfaces and conditions comply with the requirements indicated in this document; applicable industry standards; federal, provincial and local regulations, as well as good trade practices. By starting work, the Applicator/User acknowledges that the conditions are acceptable.

Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to a minimum of ICRI CSP 2 (note: ICRI CSP 3 will provide better overall performances where high shear stress from dynamic loads may be present or that can reasonably be expected).Whenever "shot-blasting" is utilized, be careful to leave concrete with a uniform texture. "Over-blasting" will result in reduced coverage rates of the primer and/or subsequent topcoats. The "shot blast" pattern may show through the last coat, known as "tracking".

Repairs to cementitious substrates, filling of blowholes, levelling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Service for recommendations in writing.

Note: Contact Sika's Technical Service for installation recommendations in writing concerning substrates or conditions not listed.

Expansion Joints

Expansion joints should be provided in the substrate at the intersection of dissimilar materials. Isolate areas subject to thermal stresses, vibration movements or around load-bearing columns and at vessel sealing rings. Communicate with Sika®'s technical services.

The owner (and architect) should discuss joint details with the flooring contractor before the job starts.

MIXING

Mixing ratio A:B = 2:3 (by volume)
IMPORTANT:

- Do not hand mix Sikafloor®-2540 W NA; mechanically mix only.
- Sikafloor®-2540 W NA must be applied as supplied.

Pre-stir Components A and B separately, making sure all solids, are evenly distributed. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin) or empty Component A into a suitably sized and clean pail and add Component B in the correct ratio. Blend the combined components thoroughly at low speed (300 - 450 rpm) for at least three (3) minutes using a drill fitted with an Exomixer® or Jiffy type paddle suited to the dimensions of the mixing container and keep the mixing paddle in the mix to avoid entrapping air. Take care not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing. Do not attempt to attend to unmixed material that may gather on the sides of the mixing container while mechanical or electrical parts are in motion. When completely mixed, Sikafloor®-2540 W NA should be uniform in appearance and consistency.

Note: Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.

APPLICATION

Apply coating by squeegee at the rate of 4 m^2/L to 5 m^2/L (163 ft^2/US gal to 203 ft^2/US gal) at 8 - 10 mil wet film thickness (w.f.t.) and back-roll
with pressure using a high quality (lint-free)
roller. Coverage will vary depending on the porosity of the prepared floor.

CLEAN UP

Clean all tools and equipment with a non-flammable solvent. Once hardened, product can only be removed mechanically.

MAINTENANCE

Sika® recommends that you consult the document: **Sikafloor® Systems_Protection, Cleaning and Maintenance Guidelines**.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

Sika Canada Inc.
Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

Other locations
Boisbriand (Quebec)
Brantford; Cambridge;
Sudbury; Toronto (Ontario)
Edmonton (Alberta)
Surrey (British Columbia)