



PRODUCT DATA SHEET

SikaFiber® Novocon® CHE-8060

Steel Fiber - Type I

PRODUCT DESCRIPTION

SikaFiber® Novocon® CHE-8060 steel fibers are designed specifically for the reinforcement of concrete. SikaFiber® Novocon® CHE-8060 is a cold drawn collated hooked end (CHE) steel fiber, to provide optimum anchorage within the concrete. SikaFiber® Novocon® CHE-8060 steel fibers are specifically designed to meet or exceed the defined performance requirements. Previously Novocon CHE7560.

WHERE TO USE

- Industrial slabs-on-ground
- Jointless slabs
- Tunnel Segments
- High strength concrete applications

CHARACTERISTICS / ADVANTAGES

- Provides uniform multi-directional concrete reinforcement
- Increases crack resistance, ductility, energy absorption or toughness of concrete
- Improves impact resistance, fatigue endurance and shear strength of concrete
- High tensile strength fiber bridging joints and cracks to provide tighter aggregate interlock resulting in increased load-carrying capacity
- Provides increased ultimate load-bearing capacity which allows possible reduction of concrete section
- Requires less labor to incorporate into concrete than conventional reinforcement
- Offers economical concrete reinforcement solutions with greater project scheduling accuracy
- Ideally suited for hand or vibratory screeds, laser screeds and all conventional finishing equipment

APPROVALS / CERTIFICATES

- Conforms to ASTM A820 /A 820M - 04, Type I cold drawn wire
- Conforms to ASTM C 1116/C 1116M, Type I fiber reinforced concrete

PRODUCT INFORMATION

Packaging

SikaFiber® Novocon® CHE-8060 fibers are available in 20 kg (44 lb) paper bags. There are 50 units or 1,000 kg (2,204 lb) bags on a pallet.

Shelf Life

If stored in dry conditions shelf life is 5 years.

Storage Conditions	The pallets should be protected against rain and snow. Do NOT stack pallets on top of each other.
Appearance / Colour	<ul style="list-style-type: none"> ▪ Fiber Type: Collated Hooked End Steel Fiber Type 1 ▪ Fiber Network: 4840 fibers/kg, (2,200 fibers/lb)
Dimensions	Length: 60 mm, 2.4 inches Diameter: 0.75 mm, (0.03 inches) Aspect Ratio: 80
Density	7.85

TECHNICAL INFORMATION

Tensile Strength	1,500 MPa (217 ksi)
-------------------------	---------------------

APPLICATION INFORMATION

Recommended Dosage	The dosage of the SikaFiber® Novocon® CHE-8060 will vary according to the type of application and the performance requirements of the project. Standard recommended dosage rate of SikaFiber® Novocon® CHE-8060 is between 15–40 kg/m ³ , (25 - 67 lbs/cu. yd.) of concrete. Dosages outside the recommended dosage range can be used to meet project specific requirements. If this is the case please contact your Sika representative for technical support.
---------------------------	--

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

Sika Canada Inc.
 Head Office
 601, avenue Delmar
 Pointe-Claire, Quebec
 H9R 4A9
 1-800-933-SIKA
 www.sika.ca

Other locations
 Boisbriand (Quebec)
 Brantford; Cambridge;
 Sudbury; Toronto (Ontario)
 Edmonton (Alberta)
 Surrey (British Columbia)

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SikaFiberNovoconCHE-8060-en-CA-(09-2023)-1-1.pdf

Product Data Sheet
 SikaFiber® Novocon® CHE-8060
 September 2023, Version 01.01
 021408011000000133

