

PRODUCT DATA SHEET

Sable Marco[®] Masonry Cement

Type N masonry cement

DESCRIPTION

Sable Marco[®] Masonry Cement is a Type N masonry cement designed to provide the required plasticity, workability, water retention, and bond integrity for masonry work. Sable Marco[®] Masonry Cement is ideal for non-load-bearing, above-grade masonry applications.

USES

Sable Marco[®] Masonry Cement is ideal for preparing mortars for use in non-load-bearing masonry applications such as laying bricks, blocks, stone veneer, and repointing, as well as for applications requiring moderate strength. It is suitable for both indoor and outdoor use in above-grade construction.

FEATURES

- Finely textured for easy mixing
- Excellent workability
- Good water retention for improved curing
- Suitable for interior and exterior, above-grade masonry work

PRODUCT INFORMATION

Packaging	30 kg (66 lb) bag
Colour	Grey
Shelf life	12 months in original unopened bag
Storage conditions	Store in a dry, covered area protected from the elements. If the product has been in contact with water or moisture or contains hardened lumps, do not use it.
Density	2,890 kg/m ³ (180 lb/ft ³)
Material temperature	Between 5 °C (40 °F) and 30 °C (86 °F)
Substrate temperature	Between 5 °C (40 °F) and 30 °C (86 °F)

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS OF USE

- Not intended for structural or load-bearing masonry, or for use in below-grade or submerged applications
- Not designed for specialized masonry mixes requiring Type S cement
- Do not use masonry cements for concrete jobs
- Mix with clean, potable water only

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Mix by volume one (1) part of Sable Marco® Masonry Cement with three (3) parts of damp, loose masonry sand. Add clean, potable water gradually while mixing to achieve a workable, plastic consistency.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sable Marco Inc
26 Chemin de la Pêche
Pont-Rouge
QC G3H 1C3