

MS-D3 is a high early strength, silica fume enhanced, pre-packaged shotcrete material for dry-process applications. This product is a pre-blended, pre-packaged, dry-process shotcrete material containing high early Portland cement, silica fume, air-entraining admixture, blended aggregates and other carefully selected components. It has greatly enhanced shooting characteristics and physical properties.

FEATURES & BENEFITS

- Improved early age strength development
- Air-entrainment provides superior resistance to freeze-thaw cycling and salt-scaling resistance
- Improved adhesive and cohesive plastic properties
- Significantly reduced rebound, resulting in lower material usage
- Improved ability to build greater thicknesses in a single pass in both vertical and overhead orientations
- Improved resistance to water wash-out
- Improved resistance to sulphate attack
- Very low permeability
- Low shrinkage
- Compatible with integral, pre-applied and/or post-applied corrosion inhibitors*
- Designed with natural normal-density non-reactive aggregates to eliminate potential alkali-aggregate reactivity (AAR)
- All KING products are manufactured using ISO 9001:2015 Certified Processes

*For more information regarding the use of a corrosion inhibitor in conjunction with MS-D3, please contact your KING Technical Representative.

OPTIONAL FEATURES & BENEFITS

ACCELERATOR LEVEL/SET-TIME/STRENGTH GAIN

- Improved performance in cold temperatures
- Improved performance in presence of running water
- Allows for earlier re-opening of traffic lanes on bridges and in subway tunnels

MS-D3 does not contain accelerator.

MS-D3 X contains a level 1 dosage of accelerator

MS-D3 X2 contains a level 2 dosage of accelerator.

MS-D3 X3 contains a level 3 dosage of accelerator.

See the Technical Data section for more detailed information.

SYNTHETIC FIBER

MS-D3 SY

- Synthetic fibers reduce cracking caused by intrinsic stresses
- Type III synthetic fiber in accordance with ASTM C 1116
- Grade FR Class I shotcrete in accordance with ASTM C 1480

CORROSION INHIBITOR

MS-D3 CI

- Corrosion inhibitor protects steel reinforcing and other metals embedded in concrete from corrosion induced by carbonation or chlorides
- Pre-blended corrosion inhibitor provides the correct dosage to enhance corrosion protection

GRADATION

- By default MS-D3 is blended to meet ACI 506 "Guide to Shotcrete", Table 1.1, Gradation No. 1
- MS-D3 G2 is blended to meet ACI 506 "Guide to Shotcrete", Table 1.1, Gradation No. 2

EXAMPLE:

For MS-D3 with a level 3 dosage of accelerator, with synthetic fibers and Gradation No. 2, the name of the product would be MS-D3 X3 SY G2.

USES

- Rehabilitation of concrete bridges, dams, reservoirs, subway tunnels, marine structures and parking ramps.
- Lining and rehabilitation of sewers and water mains.
- New construction including slope stabilization, soil-nailing, shaft and tunnel linings, pools and other concrete structures.
- Use of a predampener in conjunction with dry-process accelerated shotcrete is not recommended. Contact your KING Technical Representative for more information.

PROCEDURES

[For temperatures above 5 °C (40 °F)]

Surface Preparation (Rock Surfaces): All surfaces to be in contact with MS-D3 must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all loose or delaminated rock. Clean the area with potable water, leaving the substrate saturated but free of standing water (SSD).

Surface Preparation (Repair or Rehabilitation): All surfaces to be in contact with MS-D3 must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all loose or delaminated concrete providing a roughened surface and a minimum of 20 mm (¾ inch) clearance behind any corroded reinforcing steel. The perimeter of the repair area should be sawcut a minimum of 20 mm (¾ inch). Clean the area to be repaired with potable water, leaving the concrete saturated but free of standing water (SSD).

Application: Apply MS-D3 in accordance with the ACI 506 "Guide to Shotcrete" publication.

CURING

Curing is essential to optimize physical properties of the shotcrete and minimize plastic shrinkage. MS-D3 should be cured immediately after material has reached initial set in accordance with ACI 308 "Guide to Curing Concrete". Continuously moist cure for a minimum period of 7 days. Alternatively, moist cure for a minimum period of 24 hours and apply a curing compound that complies with ASTM C 309. Curing is particularly critical in rapid moisture loss conditions such as high temperatures, high winds and low humidity.

[For temperatures below 5 °C (40 °F)]

Use MS-D3 X2 or MS-D3 X3

Surface Preparation (Rock Surfaces): All surfaces to be in contact with MS-D3 X2 or MS-D3 X3 must be free from dust, oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all loose or delaminated rock. To avoid freezing of the interface between the shotcrete and the parent concrete, do not pre-wet the receiving surface. Pneumatically remove any free standing or other fine particles that may interfere with the bond between MS-D3 X2 or MS-D3 X3 and the substrate.

Surface Preparation (Repair or Rehabilitation): All surfaces to be in contact with MS-D3 X2 or MS-D3 X3 must be free from oil, grease or any other foreign substances that may interfere with the bond of the material. Remove all loose or delaminated concrete providing a roughened surface and a minimum of 25 mm (1 inch) clearance behind the reinforcing steel. The perimeter of the repair area should be sawcut a minimum of 20 mm (¾ inch). To avoid freezing of the interface between the shotcrete and the parent concrete, do not pre-wet the receiving surface. Pneumatically remove any free standing or other fine particles that may interfere with the bond between MS-D3 X2 or MS-D3 X3 and the substrate. Do not apply MS-D3 X2 or MS-D3 X3 when ambient temperature is below or is expected to fall below -5 °C (20 °F) within 6 hours following the application of shotcrete. Do not apply when temperature of receiving surface is below -5 °C (20 °F). Material temperature should be maintained above 10 °C (50 °F) at the time of application. Mixing water temperature should be maintained between 20 °C (70° F) and 25 °C (80 °F).

Application: Apply MS-D3 X2 or MS-D3 X3 in accordance with the ACI 506 "Guide to Shotcrete" publication.

CURING

A resin based liquid membrane curing compound approved for use in cold weather conditions should be applied immediately after shotcrete reaches final set.

TECHNICAL DATA

The following data is representative of typical values achievable using proper application techniques as outlined in the ACI 506 "Guide to Shotcrete" publication. The data was obtained during project field tests and in-house shotcrete studies.

ACCELERATOR LEVEL

	MS-D3	MS-D3 X	MS-D3 X2	MS-D3 X3
--	-------	---------	----------	----------

SET TIME* ASTM C 1117

	MS-D3	MS-D3 X	MS-D3 X2	MS-D3 X3
Initial	3 hours	45 minutes	15 minutes	3 minutes
Final	5 hours	60 minutes	25 minutes	5 minutes

COMPRESSIVE STRENGTH* ASTM C 116 (MODIFIED)

	MS-D3	MS-D3 X	MS-D3 X2	MS-D3 X3
4 Hour	-	-	2 MPa (290 psi)	7 MPa (1015 psi)
8 Hour	-	7 MPa (1015 psi)	8 MPa (1150 psi)	10 MPa (1500 psi)
12 Hour	-	10 MPa (1500 psi)	12 MPa (1750 psi)	14 MPa (2030 psi)

COMPRESSIVE STRENGTH* ASTM C 1604

1 Day	21 MPa (3000 psi)	25 MPa (3625 psi)	25 MPa (3625 psi)	25 MPa (3625 psi)
3 Day	30 MPa (4350 psi)	30 MPa (4350 psi)	30 MPa (4350 psi)	30 MPa (4350 psi)
7 Day	35 MPa (5075 psi)	35 MPa (5075 psi)	35 MPa (5075 psi)	35 MPa (5075 psi)
28 Day	42 MPa (6000 psi)	42 MPa (6000 psi)	42 MPa (6000 psi)	42 MPa (6000 psi)

FLEXURAL STRENGTH ASTM C 78

7 Day	6.5 MPa (940 psi)	6.0 MPa (870 psi)	6.0 MPa (870 psi)	6.0 MPa (870 psi)
28 Day	7.5 MPa (1085 psi)	7.0 MPa (1015 psi)	7.0 MPa (1015 psi)	7.0 MPa (1015 psi)

UNIAXIAL DRYING SHRINKAGE ASTM C 157

28 Day	500 µm/m	600 µm/m	600 µm/m	600 µm/m
56 Day	580 µm/m	650 µm/m	650 µm/m	650 µm/m

FREEZE-THAW RESISTANCE ASTM C 666

(Excellent durability factor)

	100%	96%	96%	96%
--	------	-----	-----	-----

SALT-SCALING RESISTANCE ASTM C 672

	0.2 kg/m ² (0.04 lb/ft ²)	1.2 kg/m ² (0.24 lb/ft ²)	1.2 kg/m ² (0.24 lb/ft ²)	1.2 kg/m ² (0.24 lb/ft ²)
--	---	---	---	---

MODULUS OF ELASTICITY** ASTM C 469

1 Day	20.8 GPa (3.0 x 10 ⁶ psi)
7 Day	22.0 GPa (3.2 x 10 ⁶ psi)
28 Day	25.4 GPa (3.7 x 10 ⁶ psi)

COEFFICIENT OF THERMAL EXPANSION** CRD-C 39

28 Day	8.1 x 10 ⁻⁶ /°C (4.5 x 10 ⁻⁶ /°F)
---------------	---

SPLITTING TENSILE STRENGTH** ASTM C 496

7 Day	4.4 MPa (640 psi)
28 Day	4.6 MPa (665 psi)

BOND STRENGTH BY SLANT SHEAR (MODIFIED)** ASTM C 882

7 Day	21.0 MPa (3060 psi)
28 Day	25.0 MPa (3625 psi)

Head Office

601, avenue Delmar
Pointe-Claire (Québec) H9R 4A9

Other Sites:

Boisbriand, Qc
Brantford; Cambridge; Sudbury; Toronto(ON)

Edmonton (Alberta)
Surrey (British Columbia)

TENSILE BOND STRENGTH**

ASTM C 1583

7 Day	2.2 MPa (320 psi)
28 Day	2.3 MPa (335 psi)

AIR CONTENT

ASTM C 457

6% ± 2%

MAXIMUM AIR VOID SPACING FACTOR**

ASTM C 457

300 µm

BOILED ABSORPTION**

ASTM C 642

6.0%

MAXIMUM VOLUME OF PERMEABLE VOIDS**

ASTM C 642

15.0%

CHLORIDE ION PENETRABILITY**

ASTM C 1202

700 Coulombs

*The following data was obtained under controlled conditions with material and ambient temperatures of 21 °C (70 °F). Higher or lower temperatures can respectively accelerate or delay setting time and early-age compressive strength gain.

**The following data is not affected by accelerator dosage and is applicable for all accelerator levels.

STORAGE AND SHELF LIFE

Material should be stored in a dry, covered area, protected from the elements. Unopened bags have a shelf life of 12 months.

SAFETY PROCEDURES

MS-D3 contains Portland cement. Normal safety-wear such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. Safety Data Sheets are available upon request.

OPTIMUM PERFORMANCE

- MS-D3 and MS-D3 X should not be applied when ambient, substrate and material temperatures are below 5 °C (40 °F) or above 35 °C (95 °F). MS-D3 X2 and MS-D3 X3 should not be applied when ambient and substrate temperatures are below -5 °C (20 °F) or when ambient, substrate and material temperatures are above 35 °C (95 °F).
- For adverse temperatures, follow ACI recommendations for Cold/ Hot Weather Concreting.
- Performance of in-place shotcrete relies heavily upon application techniques. To ensure optimum quality of in-place shotcrete, the material, equipment and key personnel should be pre-qualified prior to project start-up.

YIELD

- 30 KG (66 lb) bag contains approximately 0.014 m³ (0.5 ft³)
- 1000 KG (2205 lb) bag contains approximately 0.45 m³ (16.5 ft³)

PACKAGING

MS-D3 is normally packaged in 30 KG (66 lb) triple-lined bags or 1000 KG (2205 lb) bulk bags and polywrapped on wooden pallets. All KING products can be custom packaged to suit specific job requirements.

Warranty: This product is designed to meet the performance specifications outlined in this product data sheet. If the product is used in conditions for which it was not intended, or applied in a manner contrary to the written recommendations contained in the product data sheet, the product may not reach such performance specifications. The foregoing is in lieu of any other warranties, representations or conditions, expressed or implied, including, but not limited to, implied warranties or conditions of merchantable quality or fitness for particular purposes, and those arising by statute or otherwise in law or from a course of dealing or usage of trade. [REV.0014_2459121.5]

Head Office

601, avenue Delmar
Pointe-Claire (Québec) H9R 4A9

Other Sites:

Boisbriand, Qc
Brantford; Cambridge; Sudbury; Toronto(ON)

Edmonton (Alberta)
Surrey (British Columbia)