



**PRODUCT DATA SHEET**

Edition 12.2017/v1  
CSC Master Format™ 09 62 00  
SPECIALTY FLOORING

# Sikafloor® Comfort Porefiller

HIGH SOLIDS, VOC-FREE AND FLEXIBLE POLYURETHANE LEVELLING AND SEALING  
COMPOUND FOR PERMEABLE SURFACES OF SOUND INSULATING PADS IN Sika  
ComfortFloor® SYSTEMS

<b>Description</b>	Sikafloor® Comfort Porefiller is a two-component, high solids and VOC-free polyurethane compound. It is applied as a flexible and durable high quality levelling and sealing compound for granular rubber Sikafloor® Comfort Regupol-6015H mats used in Sika ComfortFloor® Pro and Sika ComfortFloor® Decorative Pro systems.	
<b>Where to Use</b>	Suitable for interior use in public and commercial buildings including: <ul style="list-style-type: none"> <li>▪ Healthcare facilities; hospitals, nursing stations, clinics, residential homes.</li> <li>▪ Educational premises; pre-schools, schools, colleges, universities.</li> <li>▪ Retail spaces; stores, superstores, showrooms.</li> <li>▪ Research areas; laboratories, corridors.</li> <li>▪ Leisure premises; museums, art galleries, theatres.</li> <li>▪ Business facilities; lobbies, passage-ways, offices.</li> </ul>	
<b>Advantages</b>	<ul style="list-style-type: none"> <li>▪ VOC-free.</li> <li>▪ Solvent-free.</li> <li>▪ Easy to apply.</li> <li>▪ Good pore sealing properties.</li> <li>▪ Non shrinking after cure.</li> <li>▪ Non flammable.</li> <li>▪ Flexible and resilient after cure.</li> </ul>	
<b>Technical Data</b>		
<b>Packaging</b>	15 L (3.96 US gal.) ready to mix kits Part R: 11.8 L (3.11 US gal.), Part H: 3.2 L (0.85 US gal.)	
<b>Colour</b>	Beige	
<b>Yield</b>	Approx. 0.5 m <sup>2</sup> /L (100 ft <sup>2</sup> /US gal.)	
<b>Shelf Life</b>	12 months in original, unopened containers when stored in dry and cool conditions (10 - 30 °C [50 - 86 °F]). The material must be conditioned at temperatures between 10 and 30 °C (50 and 86 °F) before use.	
<b>Pot Life</b>	Time	Temperature
	~ 36 minutes	10 °C (50 °F)
	~ 20 minutes	20 °C (68 °F)
	~ 12 minutes	30 °C (86 °F)
<b>Properties (Resin) at 23 °C (73 °F) and 50 % R.H.</b>		
<b>Density</b>	Mixed resin: 1.3 kg/L (11.05 lb/US gal.)	
<b>Tensile Strength DIN 53504</b>	14 days ~ 5.0 MPa (725 psi)	
<b>Shore A Hardness DIN 53505</b>	14 days ~ 89	
<b>Elongation at Break DIN 53504</b>	14 days ~ 60 %	
<b>VOC Content</b>	0 g/L	
<b>Chemical resistance</b>	Consult Sika Canada	
<i>Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.</i>		

**HOW TO USE**

**Surface**

All surfaces must be clean, sound and dry before proceeding with the installation of the Sikafloor® Comfort Porefiller.

**Preparation**

Where applying onto concrete or similar substrates, remove all dirt and dust, laitance, grease, oil, asphalt, tar, bituminous materials, grease, curing agents, impregnations, wax, foreign matter, impregnations, coatings or sealers and detritus from the surface by appropriate mechanical means, such as abrasive blast cleaning in order to achieve a contaminant-free profile equivalent to ICRI / CSP 3. Whenever abrasive blast cleaning is used, be careful to leave concrete with a uniform texture. Over blasting will result in increased consumption/reduced coverage rates of the adhesive.

All projections, rough spots etc must be ground off and the surface suitable level before proceeding. Rough surfaces need to be levelled prior to application of a self levelling/smoothing topping. Contact Sika Canada for project specific recommendations.

Following surface preparation remove all preparation residue, including dirt and loose friable material, preferably by industrial wet/dry vacuum (sweeping can result in making dust airborne to settle on the floor surface at a later juncture). This will help to ensure a tenacious bond between the primer and substrate

The compressive strength of the concrete substrate should be at least 24 MPa (3500 psi) at 28 days and at least 1.7 MPa (250 psi) in tension following preparation of the substrate at the time of application of Sikafloor® Comfort Porefiller.

**Sikafloor® Comfort Porefiller is applied onto well-adhered Sikafloor® Comfort Regupol-6015H sound insulating pads and not onto concrete of floor substrates.**

Nonetheless, surface preparation of substrates and the subsequent condition is of paramount importance to ensure that the pads remain stable and the pore filler is likewise sound.

---

**Mixing**

Pre-stir each component using a low speed drill (300 - 400 rpm) and *Jiffy* type paddle until uniform in colour and consistency. Prolonged vibration and higher ambient temperatures during transportation can result in settling of the resin component. In the case of Part R, this requires mechanical mixing for a period of at least 2 minutes to ensure that all solids are dispersed and evenly distributed.

Empty Part H into Part R and thoroughly mix for at least two (2) minutes using a low-speed drill (300 - 400 rpm) and *Jiffy* or *Exomixer*® type paddle.

**Note:** mix entire units only. While mixing, keep the mixing paddle within the resin and below the surface in order to minimize air entrapment. During the mixing operation, scrape down the sides and bottom of the pail with a flat or straight edge trowel at least once to ensure thorough mixing. Over mixing must be avoided to minimize air entrapment.

Upon completion of mixing, Sikafloor® Comfort Porefiller should be uniform in colour and consistency.

---

**Application**

Apply Sikafloor® Comfort Porefiller by pouring out the mixed material as quickly as possible within the pot-life and then spreading immediately with a flat trowel or squeegee at not less than 2.5 m<sup>2</sup>/L (100 ft<sup>2</sup>/US gal.). This will maximize the flow properties and coverage of the substrate.

**This material is classed as a continuous flooring application, during which there can be no interruptions to the mix-to-mix installation.** It is imperative that all materials and equipment be present and in working order and that all material is correctly mixed so as to enable uninterrupted works.

The cure time after which Sikafloor®-300 N or Sikafloor®-330 base coats can be applied onto Sikafloor® Comfort Porefiller will be influenced by temperature, but the following represents approximations:

Substrate Temperature	Minimum	Maximum
10 °C (50 °F)	~ 12 hours	~ 72 hours
20 °C (68 °F)	~ 8 hours	~ 60 hours
30 °C (86 °F)	~ 6 hours	~ 48 hours

**Note:** Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

---

**Clean Up**

Clean all tools and application equipment with Sika® Urethane Thinner and Cleaner immediately after use. Once hardened, product can only be removed mechanically. Wash soiled hands and skin thoroughly in hot soapy water or use Sika® Hand Cleaner towels.

---

**Limitations**

- Sika ComfortFloor® systems are best installed by skilled and experienced applicators. Consult Sika Canada for advice and recommendations.
- Prior to application, measure and confirm the following: substrate moisture content, ambient relative humidity, ambient and surface temperature and dew point. During installation, confirm and record above values at least once every three (3) hours, or more frequently whenever conditions change (e.g. ambient temperature rise/fall, relative humidity increase/decrease, etc.).
- Beware of condensation! The substrate must be at least 3 °C (5 °F) above the dew point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.
- Moisture content of concrete substrate must be ≤ 4% by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to ICRI / CSP 3). Do not apply to concrete substrate with moisture levels exceeding 4 % mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate exceeds 4 % by mass (pbw – part by weight), as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor® 1610 or Sikafloor® 81 EpoCem®<sup>CA</sup>.

- When relative humidity tests for concrete substrate are conducted per ASTM F2170 for project specific requirements, values must be  $\leq 85\%$ . If values exceed  $85\%$  according to ASTM F2170, use Sikafloor®-1610 or Sikafloor®-81 EpoCem®CA. ASTM F2170 testing is not a substitute for measuring substrate moisture content with a Tramex® CME/CMExpert type concrete moisture meter as described above.
- Do not apply while ambient and substrate temperatures are rising. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapour drive.
- Uncured material reacts in contact with water, which will result in foaming. During application, care must be taken that no sweat drops into fresh Sikafloor® Comfort Porefiller (wear head and wrist bands).
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Maximum ambient relative humidity during application and cure:  $80\%$ .
- Protect from damp, condensation and water for at least 24 hours.
- Do not apply Sikafloor® products to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor® product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Minimum/Maximum ambient and substrate temperatures:  $10\text{ }^{\circ}\text{C} / 30\text{ }^{\circ}\text{C}$  ( $50\text{ }^{\circ}\text{F} / 85\text{ }^{\circ}\text{F}$ ).
- Material temperature: Precondition material for at least 24 hours between  $18\text{ }^{\circ}\text{C}$  to  $24\text{ }^{\circ}\text{C}$  ( $65\text{ }^{\circ}\text{F}$  to  $75\text{ }^{\circ}\text{F}$ ).
- Mixing and application attempted at material, ambient and/or substrate temperature conditions less than  $18\text{ }^{\circ}\text{C}$  ( $65\text{ }^{\circ}\text{F}$ ) will result in a decrease in product workability and slower cure rates.
- Do not hand mix Sikafloor® materials. Mechanically mix only.
- Product must not be thinned/diluted as this will effect the critical time for installation of the underlayment, the cure and reduce the ultimate properties of the adhesive.
- Mechanical, chemical & physical properties will be fully achieved at full cure.

### Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN  
FOR INDUSTRIAL USE ONLY

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: [www.sika.ca](http://www.sika.ca)

#### SIKA CANADA INC.

##### Head Office

601, avenue Delmar  
Pointe-Claire, Quebec  
H9R 4A9

##### Other locations

Toronto  
Edmonton  
Vancouver

1-800-933-SIKA  
[www.sika.ca](http://www.sika.ca)

Certified ISO 9001 (CERT-0102780)  
Certified ISO 14001 (CERT-0102791)