



PRODUCT DATA SHEET

Sika® Injection-216

STRUCTURAL POLYURETHANE INJECTION RESIN

PRODUCT DESCRIPTION

Sika® Injection-216 is a 2-part, polyurethane structural injection resin. It is specially formulated for crack injection work by pressure injection.

WHERE TO USE

Sika® Injection-216 may only be used by experienced professionals.

Fills and seals voids and cracks in structures and construction elements such as:

- Bridges
- Civil engineering structures
- Tunnels
- Mines
- Industrial and residential buildings
- Water retaining structures
- Ground stabilisation
- Columns
- Beams
- Foundations
- Walls
- Floors

PRODUCT INFORMATION

Composition / Manufacturing	Polyurethane	
Packaging	Part A	9,9 kg
	Part B	12 kg
Refer to current price list for packaging variations.		

CHARACTERISTICS / ADVANTAGES

- Very good adhesion to concrete, masonry and stone.
- Suitable for dry, damp and wet conditions
- Very high mechanical properties
- Fast curing with or without water contact
- Reaction time adjustable with accelerator
- Injectable with 1-component or 2-component pumps
- Compatible with concrete, mortar, metal, plastic coated components, cable coatings, etc.
- Resistant to salts, alkali and acids present in construction components or in the ground
- Prevents the ingress of water and infiltration which can cause reinforcement corrosion

APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to EN 1504-5 - Concrete injection
- Drinking Water Approva, Sika® Injection-216, KTW- B, LADR

Colour	Part A:	yellowish
	Part B	brown
	Part A+B mixed	~ amber
Shelf Life	24 months from date of production	
Storage Conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging.	
Density	Part A	~1,0 kg/l
	Part B	~1,2 kg/l
Viscosity	~425 mPa·s (+23 °C)	
Product Declaration	EN 1504-5: Concrete injection	

TECHNICAL INFORMATION

Compressive Strength	~70 N/mm ² (7 days / +21 °C)	(ISO 604)
Tensile Strength	~30 N/mm ² (7 days / +21 °C)	(ISO 527)
Modulus of Elasticity in Tension	~1850 N/mm ² (7 days / +21 °C)	(ISO 527)
Elongation at Break	~1,9 % (7 days / +21 °C)	(ISO 527)
Reaction to Fire	B2	(DIN 4102-4)
Chemical Resistance	Resistant to salts, alkali and acids present in construction components or in the ground. Contact Sika Technical Services for additional information.	

APPLICATION INFORMATION

Mixing Ratio	A : B = 1 : 1 parts by volume	
	A : B = 1 : 1,2 parts by weight	
Substrate Temperature	> +1 °C	
Pot Life	Temperature	Time
	+10 °C	~50 minutes
	+20 °C	~25 minutes
	+30 °C	~10 minutes

The pot life begins when Parts A+B are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the pot life. To obtain longer workability at high temperatures, chill Parts A+B before mixing (not below +5 °C).

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

LIMITATIONS

- When injecting into wet environments, material will start foaming at the contact area interfaces.
- When filling large cavities / voids, the exothermic reaction of the mixed product may generate heat.

ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS

provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Crack injection: Concrete / masonry

- The substrate surface along the line of the crack capping sealer (i.e. Sikadur®-31 CF Rapid), must be sound, clean, dry or matt damp.
- It must also be free from standing water, ice, dirt, oil, grease, coatings, laitance, efflorescence, old surface treatments, all loose particles and any other surface contaminants that could affect adhesion of the capping sealer.

SUBSTRATE PREPARATION

Crack injection: Concrete / masonry

- Cracks may be dry, damp or wet, but free from standing water.
- After inserting or bonding injection ports, cap the crack with a capping sealer (i.e. Sikadur®-31 CF Rapid) and allow to cure.
- Remove any standing water by oil free compressed air.
- Remove contaminants by purging crack with resin until the resin runs clean and contaminant free.

MIXING

IMPORTANT: Mix full units only.

IMPORTANT: Avoid over-mixing to minimise air entrainment.

Requirement: Use a low speed electric single paddle mixer and stirrer (300–400 rpm) for mixing

Note: Mix only the quantity that can be used within its pot life.

1-Component pump

1. Add Parts A + B into a clean, dry mixing container.
2. Mix Parts A + B continuously for ~2,0 minutes until a uniformly coloured mix is achieved.
3. Add mixed resin into the pump's hopper.

2-Component pump

1. Add Part A and Part B into the 2 separate pump dispensers.
2. Set the metering ratio of the pump to: A : B = 1 : 1 parts by volume A : B = 1 : 1,2 parts by weight
3. Parts A + B will be mixed automatically by the pump's mixing head (static-mixing element).

Sika Canada Inc.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

Other locations

Boisbriand (Quebec)
Brantford; Cambridge;
Sudbury; Toronto (Ontario)
Edmonton (Alberta)
Surrey (British Columbia)

APPLICATION METHOD / TOOLS

- Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.
- Preliminary trials must be carried out by a competent applicator to establish suitability of resin, packer spacing (for crack injection), injection equipment and pressure.

CLEAN UP

- Clean all tools and equipment using the Sika® Injection Cleaning System. Refer to the Product Data Sheet.
- Use Sika® Injection Cleaner C1 for pump cleaning of non-cured resin. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any other recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

Product Data Sheet

Sika® Injection-216
September 2021, Version 01.01
020707010020000044

