

PRODUCT DATA SHEET

Sika® ViscoCrete®-6100

HIGH RANGE WATER REDUCING ADMIXTURE

PRODUCT DESCRIPTION

Sika® ViscoCrete®-6100 is a high range water reducing and superplasticizing admixture utilizing Sika's ViscoCrete® polycarboxylate polymer technology.

WHERE TO USE

- Sika® ViscoCrete®-6100 is designed for conventional precast/prestress applications, and may also be used for the production of Self-Consolidating Concrete (SCC).
- Sika® ViscoCrete®-6100 is a high range water reducer that provides excellent plasticity, and may be combined with accelerator or retarder admixture to control the set time and slump life.

CHARACTERISTICS / ADVANTAGES

Water Reduction: Sika® ViscoCrete®-6100 can be dosed in small amounts to obtain water reduction from 10–15 %, and will achieve water reduction up to 45 % at high dosage rates. Sika® ViscoCrete®-6100 is suitable for all levels of water reduction.

High Plasticity and Cohesion: The superplasticizing action of Sika® ViscoCrete®-6100 provides high-slump, flowing concrete that maintains excellent workability, and may be placed with minimal or no vibration even at very low water cement ratios as low as 0.25. Sika® ViscoCrete®-6100 maintains excellent cohesion within the concrete matrix, and eliminates excessive bleeding or segregation. The unique plasticizing effect of Sika® ViscoCrete®-6100 provides excellent formed surface finish.

PRODUCT INFORMATION

The combined high range water reduction and superplasticizing action of Sika® ViscoCrete®-6100 provide the following benefits in hardened concrete:

- Higher early compressive strengths for earlier removal of forms and structural use of concrete
- Higher ultimate strengths allow for greater engineering design flexibility and structural economies
- Reduced water cement ratios produce more durable, dense concrete with reduced permeability
- Highly effective plasticizer reduces surface defects in concrete elements and improves aesthetic appearance
- Ideal for the production of Self-Consolidating Concrete (SCC)
- Ideal for ready-mix trucks
- Formulated to provide maximum water reduction, increased early strength, improved finishing characteristics, especially when a broom is desired
- Sika® ViscoCrete®-6100 does not contain formaldehyde, calcium chloride or any other intentionally added chlorides, and will not initiate or promote the corrosion of steel present in the concrete

APPROVALS / CERTIFICATES

- Sika® ViscoCrete®-6100 meets the requirements for ASTM C494 Types A and F.
- Approved by the Ontario Ministry of Transportation (MTO)
- Approved by the Ministère des Transports du Québec (MTQ)

Packaging	205 L (54 US gal.) drum 1040 L (275 US gal.) IBC Bulk delivery
Appearance / Colour	Liquid / Amber
Shelf Life	1 year when stored in dry warehouse conditions at temperatures between 10 °C and 27 °C (50 °F and 80 °F).
Storage Conditions	Store in dry conditions above 5 °C (40 °F). If frozen, thaw and agitate thoroughly to return to normal state.
Specific Gravity	Approx. 1.09

APPLICATION INFORMATION

Recommended Dosage

Dosage rates will vary according to materials used, ambient conditions and the requirements of a specific project. Sika recommends dosage at 195–520 mL/100 kg (3–8 fl.oz. per 100 lb) of cementitious for general concrete applications. If maximum water reduction is required dosage up to 780 mL/100 kg (12 fl.oz./100 lb) of cementitious may be used.

Dosage rates outside the recommended range may be used where specialized materials such as microsilica are specified, extreme ambient conditions are encountered or unusual project conditions require special consideration. In this case, please contact your Sika Canada Technical Sales Representative for more information and assistance.

Mixing

For best superplasticizing results, add Sika® ViscoCrete®-6100 directly to freshly mixed concrete in the concrete mixer at the end of the batching cycle. Sika® ViscoCrete®-6100 may also be dispensed as an integral material during the regular admixture batching cycle, or into freshly mixed concrete in a ready-mix truck, at the concrete plant. To optimize the superplasticizing effect after the addition of Sika® ViscoCrete®-6100, Sika recommends that the combined materials be mixed for 60–80 revolutions either in the concrete mixer or in the ready-mix truck.

Do not introduce Sika® ViscoCrete®-6100 directly onto dry cementitious materials.

Combination with other admixtures: Sika® ViscoCrete®-6100 is highly effective as a single admixture or in combination with other admixtures in the Sika system. If used in combination with certain Sikament® high range water reducers it may affect the plastic properties of fresh concrete. Contact a Sika Canada Technical Sales Representative for further information.

Combination with Microsilica: Sika® ViscoCrete®-6100 is particularly well suited for use with microsilica because of its water reduction capability.

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

Sika Canada Inc.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

Other locations

Boisbriand (Quebec)
Brantford; Cambridge;
Sudbury; Toronto (Ontario)
Edmonton (Alberta)
Surrey (British Columbia)

Product Data Sheet

Sika® ViscoCrete®-6100
November 2021, Version 01.01
02130101100000144

SikaViscoCrete-6100-en-CA-(11-2021)-1-1.pdf

