



PRODUCT DATA SHEET

SikaFix®-210

POLYURETHANE RESIN FOR INJECTION SEALING AND GROUND STABILIZATION IN TUNNELLING AND MINING

PRODUCT DESCRIPTION

SikaFix®-210 is a fast-reacting polyurethane based resin with short gel times and high final strength.

WHERE TO USE

SikaFix®-210 may only be used by experienced professionals.

SikaFix®-210 is used for permanent and durable injection sealing and ground stabilization of the headings in tunnel construction and mining. SikaFix®-210 is also used for stabilization of other loose rock faces, voids and unstable surfaces. It is suitable for injection in dry, damp and wet conditions, including sealing around water-bearing zones in rock, masonry dams and tunnel walls etc. SikaFix®-210 can be accelerated with SikaFix® AC-21 for waterstopping applications during construction works i.e. for unexpected water inrush. In situations with high water inrush and if a faster foaming action is necessary, the mixture of SikaFix®-210 and SikaFix® AC-21 can be further accelerated by the addition of SikaFix® AC-21 SF.

CHARACTERISTICS / ADVANTAGES

- High final strength
- Foaming on contact with water (~ 3 times volume increase)
- Very fast curing
- Modular system with SikaFix AC-21 and SikaFix AC-21 SF
- Easy application due to volume ratio 1:1
- High penetration ability
- Low initial viscosity
- CFC- and halogen-free
- Total solid*

* acc. to testing method of German Institute "Deutsche Bauchemie e.V."

APPROVALS / CERTIFICATES

German KTW drinking water certificate

PRODUCT INFORMATION

Composition / Manufacturing

2-component Polyurethane resin, solvent and CFC-free

Packaging

Part A:	20.20 kg
Part B:	24.80 kg
Part A (IBC):	980 kg
Part B (IBC):	1200 kg

Shelf Life

12 months shelf life from date of production if stored properly in undamaged,

Product Data Sheet

SikaFix®-210

January 2023, Version 02.01

020707010020000009

unopened, original sealed packaging.

Storage Conditions	Dry storage at temperatures from +5 °C up to +35 °C. Protect from direct sunlight and humidity.		
Colour	Part A: Slightly yellow Part B: Black brown		
Density	Part A: ~1.01 kg/l at 23 °C	Part B: ~1.23 kg/l	(ISO 2811)
Flash Point	Part A: >140 °C	Part B: ~250 °C	(DIN 53213)
Viscosity	Part A: ~ 300 mPa·s At 23 °C	Part B: ~ 260 mPa·s	(acc. ISO 3219)

TECHNICAL INFORMATION

Shore A Hardness	~80 (3 days)	(EN 868)
Compressive Strength	~ 80 ±5 N/mm ²	(ISO 604)
Tensile Strength in Flexure	~70 N/mm ² (3 days at 23 °C)	(ISO 178)

APPLICATION INFORMATION

Mixing Ratio	1 : 1 parts by volume (refer to Application Instructions)	
Ambient Air Temperature	+5 °C min. / +35 °C max.	
Substrate Temperature	+5 °C min. / +35 °C max.	
Pot Life	~ 45 seconds (at 23 °C)	(PM 10081-11)

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

LIMITATIONS

Only for application by trained and experienced professionals.

ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

- SikaFix[®]-210 is supplied in containers pre-batched according to the required mixing ratio of 1 : 1 parts by volume
- Both components are mixed together on injection through a 2 C-injection pump, drawing each component directly from the original containers. The static mixer must be suitable to ensure that the mixture of comp. A and B forms a stable emulsion.
- Use injection ports, lances or packers with a sufficiently large diameter and flow.

APPLICATION METHOD / TOOLS

Two component injection pumps suitable for PU-Injection. For detailed information, please refer to the corresponding method statement.

CLEAN UP

Clean all tools and application equipment according to the Product Data Sheet for the Sika® Injection Cleaning System.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

Sika Canada Inc.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

Other locations

Boisbriand (Quebec)
Brantford; Cambridge;
Sudbury; Toronto (Ontario)
Edmonton (Alberta)
Surrey (British Columbia)

Product Data Sheet

SikaFix®-210
January 2023, Version 02.01
020707010020000009

