

Product Data Sheet

Version 09/2010 (03/2015)

Sika® Aktivator-100

(formerly Sika® Aktivator)

Technical Data

Chemical Base	Solvent-based adhesion promoter
Colour	Yellow/amber, clear
Density (CQP ¹ 006-3/ISO 2811-1)	Approx 0.71 kg/l
Viscosity ² (CQP 029-3/ISO 3219)	Approx 2 mPa's
Flash Point (CQP 007-1/ISO 13736)	-4°C (25°F)
Application Temperature	5°C to 35°C (40°F to 95°F)
Application Method	Wipe on with cotton rag or paper towel
Coverage	Approx. 40 ml/m ²
Flash-off Time ^{2,3}	Below 15°C - 30 minutes Above 15°C - 10 minutes Maximum - 2 hours
Storage	Store in sealed container in a cool, dry place
Shelf Life	12 months
¹ CQP = Corporate Quality Procedures. ² 23°C and 50% relative humidity. ³ Drying time may be affected by temperature and specific applications.	

Description

Sika® Aktivator-100 is an activating agent to improve adhesion. It is specifically formulated for the treatment of bond faces in direct glazing work prior to application of various Sika polyurethane adhesives. Sika® Aktivator-100 is manufactured in accordance with ISO 9001 and ISO 14001 Quality Assurance Systems.

Product Benefits

Cleans and improves adhesion on non-porous surfaces which are to be adhered using Sikaflex® products.

Areas of Application

Sika® Aktivator-100 improves adhesion on glass, ceramic-coated glass, the cut-face of old polyurethane adhesive, polyurethane pre-applied windows, glass and paints. This product is suitable for professional, experienced users only. Testing with actual substrates and conditions has to be performed to ensure adhesion and material compatibility.

Method of Application

Wipe bond faces with a clean lint-free cloth or absorbent paper towel moistened with Sika® Aktivator-100. Apply Sika® Aktivator-100 sparingly, and apply once only. Immediately wipe-off any excess with a clean, dry cloth or paper towel. Ideal application and surface temperature is between 15°C and 25°C. Tightly re-seal the container immediately after each use.

Important Note

Sika® Aktivator-100 contains solvent which may dull the surface finish of some freshly applied paints. Preliminary trials should be carried out. **Never apply onto a porous substrate.** The cleaner may not dry completely on porous surfaces, preventing the adhesive or sealant from curing properly. Where necessary, adjacent porous surfaces should be masked. Sika® Aktivator-100 should be used within one month of opening the can. Discard any Sika® Aktivator-100 after this time or earlier if it has become opaque or cloudy. Prolonged exposure to atmospheric moisture will cause Sika® Aktivator-100 to become inactive. Sika® Aktivator-100 must not be used for removing or tooling uncured Sikaflex® polyurethane products.



Industry

Further Information	Working instructions for a defined application may require information beyond that which is supplied in this Product Data Sheet. Copy of the following publications are available upon request: <ul style="list-style-type: none">- Material Safety Data Sheet- Sika Pre-treatment Chart
Packaging	Bottles of 250 ml and 1 litre.
Value Bases	All technical data stated in this Product Data Sheet are laboratory test-based. Current measured values may vary due to factors beyond our influence.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the current Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data for the appropriate type of substance. All Product Data Sheets and Material Safety Data Sheets are available on our website at: www.sika.ca .

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelf life. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed in the Internet under www.sika.ca.

Sika Canada Inc.
601 Delmar Avenue
Pointe-Claire, QC H9R 4A9
Tel.: 514-697-2610
Fax: 514-697-3910

1-800-689-SIKA
www.sika.ca

An ISO 9001 certified company
Pointe-Claire : ISO 14001 certified EMS

