

PRODUCT DATA SHEET

Sikaplan® Adhered-60 EnergySmart

THERMOPLASTIC PVC ROOF MEMBRANE

PRODUCT DESCRIPTION

Sikaplan® Adhered-60 EnergySmart is a thermoplastic PVC roof membrane designed with an integral fibreglass mat reinforcement.

WHERE TO USE

Sikaplan® Adhered-60 EnergySmart is adhered to approved substrates.

Areas of Application

- Adhered roof systems
- Adhered roof flashings
- New construction and reroofing

CHARACTERISTICS / ADVANTAGES



- Integral fibreglass mat reinforcement for excellent dimensional stability
- Heat welded seams for strength and security

APPROVALS / CERTIFICATES

- FM Global
- Underwriters Laboratories
- Underwriters Laboratories of Canada
- ICC Code Compliance – ES 1157
- Miami-Dade County
- Florida Building Code
- California Title 24
- LEED / Green Globes
- CSA-A123.21

PRODUCT INFORMATION

Recycled content	9 % Pre-consumer, 1 % Post-consumer	
Reinforcing Material	Fibreglass	
Packaging	1.5 mm (60 mil) Membrane 3 m x 30 m (10 ft x 100 ft) roll, 158 kg (348 lb) per roll, 8 rolls per pallet 1.5 m x 30 m (5 ft x 100 ft) roll, 79 kg (174 lb) per roll, 12 rolls per pallet	
Appearance / Colour	<ul style="list-style-type: none"> ▪ Top: White, Reflective Grey, and Tan ▪ Bottom: Dark Grey 	
Shelf Life	Not applicable	
Storage Conditions	Store rolls on pallets and fully protected from the weather with clean canvas tarpaulins. Unvented polyethylene tarpaulins are not accepted due to the accumulation of moisture beneath the tarpaulin in certain weather conditions that may affect the ease of membrane weldability.	
Overall Thickness	1.5 mm (60 mil) nominal 1.14 mm (45 mil)	(ASTM D751) (ASTM Type II D4434 Spec. Requirement)
Thickness Above Scrim	0.6 mm (24 mil) 0.4 mm (16 mil)	(-) (ASTM Type II D4434 Spec. Requirement)

TECHNICAL INFORMATION

Resistance to Static Puncture	Pass 15 kg (33 lbf)	(ASTM D5602) (ASTM Type II D4434 Spec. Requirement)
Resistance to Dynamic Puncture	Pass 10 J (7.3 ft-lbf)	(ASTM D5635) (ASTM Type II D4434 Spec. Requirement)
Tensile Strength	285 N (64 lbf/in) 245 N (55 lbf/in) 276 N (62 lbf/in) 245 N (55 lbf/in)	(ASTM D751), M.D. ¹ (ASTM Type II D4434 Spec. Requirement) (ASTM D751), C.M.D. ¹ (ASTM Type II D4434 Spec. Requirement)
¹ M.D. = Machine Direction, C.M.D. = Cross Machine Direction.		
Elongation at Break	250 % & 220 % 250 % & 220 %	(ASTM D751), M. D.1 & C.M.D. ¹ (ASTM Type II D4434 Spec. Requirement)
¹ M.D. = Machine Direction, C.M.D. = Cross Machine Direction.		
Linear Dimensional Change	-0.02 % 0.1 % max.	(ASTM D1204) (ASTM Type II D4434 Spec. Requirement)
Tear Strength	67 N (15 lbf) 45 N (10 lbf)	(ASTM D1004) (ASTM Type II D4434 Spec. Requirement)
Seam Strength	Pass 75 % of original ²	(ASTM D751) (ASTM Type II D4434 Spec. Requirement)
² Failure occurs through membrane rupture not seam failure.		
Low Temperature Flexibility	Pass Pass	(ASTM D2136), -40 °C (-40 °F) (ASTM Type II D4434 Spec. Requirement)
Retention of Properties after Heat Ageing	Tensile Strength, % of original: Pass Elongation, % of original: Pass Tensile Strength, % of original: 90 Elongation, % of original: 90	(ASTM D751) (ASTM D751) (ASTM Type II D4434 Spec. Requirement) (ASTM Type II D4434 Spec. Requirement)

Resistance to UV Exposure	10,000 hours	(ASTM G154)
	5,000 hours	(ASTM Type II D4434 Spec. Requirement)
	Cracking (7x magnification)	None
	Discoloration (by observation)	Negligible
	Crazing (7x magnification)	None

Weight Change after Immersion in Water	2.4 %	(ASTM D570)
	± 3.0 %	(ASTM Type II D4434 Spec. Requirement)

Solar Reflectance	EnergySmart Colours	Initial Solar Reflectance¹	3-Year Solar Reflectance¹
	EnergySmart White		0.85
EnergySmart Tan		0.72	0.65 ²
EnergySmart Reflective Grey		0.73	0.65 ²

¹ Solar Reflectance testing according to ASTM C1549.

² CRRC Rapid Ratings: These are interim laboratory-aged values that simulate weathered values. These values will be replaced with the measured three-year aged values upon completion of the weathering process. SRI values calculated using Rapid Ratings may change once the aged rating replaces the interim rating.

Thermal Emittance	EnergySmart Colours	Initial Thermal Emittance¹	3-Year Thermal Emittance¹
	EnergySmart White		0.89
EnergySmart Tan		0.89	0.88 ²
EnergySmart Reflective Grey		0.89	0.88 ²

¹ Thermal Emittance testing according to ASTM C1371, Slide Method.

² CRRC Rapid Ratings: These are interim laboratory-aged values that simulate weathered values. These values will be replaced with the measured three-year aged values upon completion of the weathering process. SRI values calculated using Rapid Ratings may change once the aged rating replaces the interim rating.

Solar Reflectance Index	EnergySmart Colours	Initial Solar Reflectance Index	3-Year Solar Reflectance Index
	EnergySmart White		107
EnergySmart Tan		88	78 ¹
EnergySmart Reflective Grey		90	78 ¹

¹ CRRC Rapid Ratings: These are interim laboratory-aged values that simulate weathered values. These values will be replaced with the measured three-year aged values upon completion of the weathering process. SRI values calculated using Rapid Ratings may change once the aged rating replaces the interim rating.

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

OTHER DOCUMENTS

Availability

Sikaplan® Adhered-60 EnergySmart is available directly from Sika Canada Authorized Applicators when used within a Sika® Sarnafil® Roofing or Waterproofing System. Contact Sika Canada or visit our website at www.sika.ca for further information.

Warranty

Upon successful completion of the installed roof by the Sika Canada Authorized Applicator, Sika Canada can provide a warranty to the Building Owner via the Authorized Applicator.

LIMITATIONS

- Ambient Air Temperature: -20 °C (-4 °F) min. / 60 °C (140 °F) max. during application
- Substrate Temperature: -30 °C (-22 °F) min. / 60 °C (140 °F) max. during application
- Not to be applied directly to polystyrene products
- Sarnafil® membranes are incompatible with asphalt, coal tar, heavy oils, roofing cements, creosote and some preservative materials.

ENVIRONMENT, HEALTH & SAFETY

This product is a manufactured article that does not require Safety Data Sheets to be marketed, transported or applied at the jobsite, according to the Hazardous Product Act - Section 2. Based on our current knowledge, this product is not classified as dangerous and does not contain any hazardous materials. Always wear personal protective equipment (including safety goggles and gloves) to manipulate and install Sika® products.

APPLICATION INSTRUCTIONS

APPLICATION

Sikaplan® Adhered-60 EnergySmart is installed after proper preparation of the approved substrate. The membrane is unrolled into approved Sikaplan or Sarnacol adhesive in accordance with Sika's technical requirements and then pressed into place with a minimum 45 kg (100 lb) steel roller. Sikaplan® Adhered-60 EnergySmart seams are heat-welded together by trained operators using hot-air welding equipment. Different Sarnacol® adhesives require different application methods. Consult Sika's Specifications or Applicator Handbook for detailed installation procedures.

Sika Canada Inc.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

Other locations

Boisbriand (Quebec)
Brantford; Cambridge;
Sudbury; Toronto (Ontario)
Edmonton (Alberta)
Surrey (British Columbia)

MAINTENANCE

As a prudent preventative measure, Sika Canada recommends that the Owner or that the Owner's designated representative inspect the installed roof system for damage, flashings, plugged drains, weathered sealants, etc. at least twice a year and after each storm.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SikaplanAdhered-60EnergySmart-en-CA-(11-2021)-5-1.pdf

Product Data Sheet

Sikaplan® Adhered-60 EnergySmart
November 2021, Version 05.01
020905051100153002

