



BUILDING TRUST  
CONSTRUIRE LA CONFIANCE



## CANADIAN TECHNICAL BULLETIN 013

TARGET MARKET ROOFING

October 31, 2021 / FOR IMMEDIATE RELEASE

---

### **Subject:** Sarnacol® 2163 – Cold Weather Application

Sarnacol® 2163 Adhesive is a two component foamable polyurethane board adhesive, has no temperature limitation and can be applied at any temperature when stored properly prior to use.

Keep temperature of content between 18 °C to 29 °C (65 °F to 85 °F) for a minimum of 24 hours prior to use. The adhesive should remain in a warm storage area until ready for use on the rooftop. In extreme conditions it may be necessary to rotate the adhesive from a hot box or warm storage area to the rooftop during application in order to maintain an appropriate application temperature.

Storing the adhesive below the recommended temperature range prior to use can have a negative effect on product performance which may include reducing the expected coverage rates of the adhesive and can, in some cases, alter the mix of the two components. Applying improperly stored material can also cause excessive stress and strain to the application equipment and packaging.

If the adhesive is exposed to cooler temperatures for an extended period, it must be brought back up to the recommended application temperatures prior to use.

All work surfaces should be clean, dry, free of dirt, dust, debris, oils, un-adhered coatings, deteriorated membranes, and other contaminants that may result in a surface that is not sound.

Refer to the Product Data Sheet for additional information such as Application instructions and limitations.

Please contact Sika Canada Roofing Technical Department for further information.