

## PRODUCT DATA SHEET

# Sable Marco® Cold Asphalt

Cold asphalt for patching potholes and asphalt surfaces

### DESCRIPTION

Sable Marco® Cold Asphalt is a pre-blended, ready-to-use cold asphalt. It is specifically designed for repairing asphalt surfaces, including potholes and utility cuts, and can be applied directly from the bag into the damaged area without heating. Once placed, it can be compacted to restore a smooth, durable surface.

### USES

Sable Marco® Cold Asphalt is ideal for repairing asphalt surfaces with thicknesses ranging from 2.5 cm (1 in) to 10 cm (4 in), covering areas up to 0.4 m<sup>2</sup> (4 ft<sup>2</sup>). It can be used to repair potholes, wide cracks, or sunken areas. Sable Marco® Cold Asphalt is suitable for asphalt driveways, walkways, and parking areas. It is not recommended for use on curbs, speed bumps and ramps, or for new driveways extensions.

### FEATURES

- Ready-to-use cold asphalt, no heating required
- Easy to apply directly from the bag
- Easily compacted to create a smooth repair
- Ideal for potholes, wide cracks, and sunken areas

### PRODUCT INFORMATION

Packaging	30 kg (66 lb) bag
Colour	Black
Shelf life	12 months in original unopened bag
Storage conditions	Store in a dry, covered area protected from the elements. Compaction from storage does not change the workability.
Yield	Approx. 0.014 m <sup>3</sup> (0.5 ft <sup>3</sup> ) per 30 kg (66 lb) bag

### BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### LIMITATIONS OF USE

- Use for repairs up to 0.4 m<sup>2</sup> (4 ft<sup>2</sup>).
- In cold weather, keep the bag in a warm place for at least 24 hours before use.
- Not recommended for use on curbs, speed bumps and ramps, or for new driveway extensions.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

Remove all damaged asphalt to a depth of 5 cm (2 in) to 10 cm (4 in) and square up the edges. Clear the area of loose debris, dust, mud, grass, or any unsound base material. For deeper holes, fill with gravel to the appropriate depth.

### APPLICATION

Pour Sable Marco® Cold Asphalt into the prepared area, slightly overfilling approximately 1.3 cm (½ in) above surrounding asphalt. Compact thoroughly using a hand tamper or plate compactor. For deep repairs, place and compact in layers not exceeding 5 cm (2 in) thick. The final repair should not exceed 10 cm (4 in) in depth.

### CURING TREATMENT

The repaired area is generally usable after 3–7 days. Hardening may take longer in warm weather. Allow 60–90 days curing time before applying a driveway sealer. Follow the sealer manufacturer's instructions.

### CLEANING OF EQUIPMENT

Clean tools immediately after use with mineral spirits.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sable Marco Inc**  
26 Chemin de la Pêche  
Pont-Rouge  
QC G3H 1C3

**PRODUCT DATA SHEET**  
Sable Marco® Cold Asphalt  
October 2025, Version 01.01  
020201010030000257