



PRODUCT DATA SHEET

SikaRepair[®]-225

1-COMPONENT, CEMENTITIOUS, FIBRE-REINFORCED SPRAYABLE MORTAR FOR STRUCTURAL REPAIRS

PRODUCT DESCRIPTION

SikaRepair[®]-225 is a 1-component, pre-packaged, ready-to-use, cementitious, silica fume, fibre-reinforced, high strength, shrinkage-compensated mortar. Formulated for application by low pressure spray. It is designed especially for repair of overhead and vertical surfaces.

WHERE TO USE

- High performance repair mortar for wet spray application. Suitable for new construction, repairs and maintenance work
- Above and below grade on concrete and mortar.
- Vertical and overhead surfaces
- Structural repair material for parking structures, industrial plants, walkways, bridges, tunnels, ramps, and dams etc.

CHARACTERISTICS / ADVANTAGES

- Ready-to-use, one-component material
- Easy to prepare, just add water
- Sprayable system
- Superior workability. Can be troweled and screeded after application
- Labour-saving system
- Superior abrasion resistance over conventional cement mortar
- Bond strength ensures superior adhesion.
- Not a vapour barrier
- Compatible with coefficient of thermal expansion of concrete
- Increased resistance to de-icing salts
- Good freeze/thaw resistance
- Very low shrinkage
- Silica fume enhanced
- Fibre-reinforced
- Formulated with inert, non-reactive aggregates to eliminate potential Alkali-Aggregate Reactivity (AAR)
- Compatible modulus of elasticity to concrete generally used for building/facade construction

PRODUCT INFORMATION

Packaging	25 kg (55 lb) bag
Shelf Life	12 months
Storage Conditions	Store (unopened) in a dry place at temperatures between +5 °C and +32 °C (41 °F and 89 °F). For best results, condition product at temperatures between +18 °C and +29 °C (65 °F and 84 °F) before using.
Appearance / Colour	Powder / Concrete Grey

Compressive Strength

1 day	23 MPa (3 335)	(ASTM C109)
7 days	35 MPa (5 076)	~MPa (~psi)
28 days	55 MPa (7 977)	Mixing Ratio 1:6.4

Temperature	+23 °C (73 °F)	+23 °C (73 °F)	(ASTM C109)
Dosage	1 bottle (150 mL)	2 bottles (300 mL)	~MPa (~psi)
12 hours	3 (435)	5 (728)	(tested with Sikacem® Accelerator)
1 day	24 (3 480)	29 (4 205)	
3 days	28 (4 060)	31 (4 495)	
28 days	54(7 830)	56 (8 208)	

Note: All moulds, mixing tools and powder components were pre-conditioned to the test temperatures. Prepared test specimens were cast and then cured at the indicated test temperatures until the time of testing.

Sikacem® Accelerator added to mix water (water content = 3.32 L (0.87 US gal.) + 1 bottle of Sikacem® Accelerator; water content = 3.14 L (0.82 US gal.) + 2 bottles of Sikacem® Accelerator).

Flexural rigidity	~7 MPa (~1 015 psi)	(ASTM C348) 28 days
Splitting Tensile Strength	~5.2 MPa (~754 psi)	(ASTM C496) 28 days
Mixing Ratio	Mix mortar with approx. 3.5 - 3.9 L (0.9 - 1.0 US gal.) of water per 25 kg (55 lb) bag.	
Yield	Approx. 13 L (0.459 ft ³) General guidance: Allow 22 - 25 kg/m ² (4.5 - 5 lb/ft ²) per 12 mm (1/2 in) applied thickness.	
Initial Set Time	2 - 3 h	(ASTM C266)
Final Set Time	5 h - 6 h 30 min	(ASTM C266)

BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods. Properties tested at +23 °C (73 °F) / 50 % r.h. unless stated otherwise.

LIMITATIONS

- **Important:** protect stored material from exposure to rain, condensation and high humidity as moisture may penetrate packaging, causing lumps.
- For best results, condition product to 18 °C to 29 °C (65 °F to 84 °F) prior to mixing and installation. Lower temperatures may result in slower strength development and longer cure times.
- Vertical applications: SikaRepair®-225 can be spray applied up to 50 mm (2 in) thickness in one lift.
- Overhead applications: Thickness should be no more than 25 - 38 mm (1 - 1 1/2 in) per pass.
- If repair requires several lifts [over 38 mm (1 1/2 in)], each lift must be applied as soon as the previous lift will support it.

- Minimum application thickness: 10 mm (3/8 in).
- Maximum total applied thickness should not exceed 76 mm (3 in) without additional reinforcing support.
- Minimum ambient and surface temperature: +7 °C (44 °F) and rising at time of application.
- Protect newly applied mortar from rain and freezing.
- Use only potable water.

ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

SURFACE PREPARATION

Remove all deteriorated concrete, dirt, oil, grease or any contaminants or conditions that may reduce performances or proper bonding. Following ICRI Guideline 310.2, the concrete surface must be clean, sound and mechanically prepared to obtain a surface profile of CSP 6 – 10 (ex : hydrodemolition, scarification, scabbling + sandblasting, etc.). Follow ICRI Guideline

Product Data Sheet

SikaRepair®-225

January 2023, Version 01.01

020302040030000052

BUILDING TRUST
CONSTRUIRE LA CONFIANCE



310.1 for the preparation of the repair perimeter, the repair area geometry and for the cleaning of the concrete and reinforcing steel surfaces. Verify the absence of micro cracking following ICRI Guideline 310.2. Dampen surface to be repaired with clean water. Substrate should be saturated surface dry (SSD) with no standing water during application.

MIXING

Conventional wet-process shotcreting equipment such as the low-pressure Moyno spray or screw type machine should be used. Set up wet-process shotcrete equipment; then add the water directly into mixer. Start the mixer in motion and add SikaRepair-225 mortar while continuing to mix. Mix to uniform consistency (approx. three (3) minutes after all ingredients are added).

APPLICATION

At time of application, surfaces should be saturated surface dry (SSD) but hold no standing water. Apply SikaRepair®-225 powder by low pressure spraying to repair vertical or overhead surfaces. Shoot SikaRepair®-225 perpendicular to the surface. This minimizes rebound, creates the smoothest pattern (reduces “bumps”) and properly encases the rebars. The velocity of SikaRepair®-225 is sufficient if, at a distance of 450 - 600 mm (18 - 24 in), SikaRepair®-225 pattern flattens out on contact with the surface and the rebars are encased. After applying SikaRepair®-225, allow it to stiffen sufficiently before shaving or finishing. Before applying the next layer, allow SikaRepair®-225 to set sufficiently so as not to disturb the preceding layer. This will take anywhere from 45 minutes to several hours, depending on mix consistency, and ambient temperature, wind conditions and humidity. Begin and finish a given patch on the same day.

CURING TREATMENT

As per ACI 308 recommendations for cement concrete, curing is required. To achieve performance consistent with Technical Data, curing must be provided by recognized curing methods, such as wet burlap covered with white polyethylene film or approved water-based curing compound, such as Sika® Florseal WB-18 & -25. Alternatively, the use of Sika® Ultracure DOT™ or NCF™ wet curing blankets is strongly recommended. Curing must commence immediately after placing and finishing. Moist-curing must be maintained for the first 24 hours

Sika Canada Inc.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

Other locations

Boisbriand (Quebec)
Brantford; Cambridge;
Sudbury; Toronto (Ontario)
Edmonton (Alberta)
Surrey (British Columbia)

only. Protect freshly applied mortar from direct sunlight, wind, rain and frost.

CLEAN UP

Clean all tools and equipment after use with water. Once hardened, the product can only be removed manually or mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

Product Data Sheet

SikaRepair®-225
January 2023, Version 01.01
020302040030000052

