



PRODUCT DATA SHEET

Edition 04.2019/v1
CSC Master Format™ 03 53 19 (03 54 16)
CONCRETE OVERLAYMENT

Sikafloor® Level-25^{CA}

CEMENTITIOUS SELF-LEVELLING FLOOR SCREED

Description	Sikafloor® Level-25 ^{CA} is a one component, polymer modified, versatile and durable floor pumpable cementitious screed for interior concrete floors which can be applied manually or by pump to achieve rapid, flat, economic substrate levelling prior to the application of the final floor finish. Typical application thickness 5 - 25 mm (3/16 - 1 in).
Where to Use	<ul style="list-style-type: none"> ▪ Factories ▪ Commercial buildings ▪ Cellars ▪ Corridors ▪ Warehouses ▪ Hospitals ▪ Domestic ▪ Fast track construction ▪ Levelling pre-cast concrete slabs
Advantages	<ul style="list-style-type: none"> ▪ Self-levelling and highly fluid ▪ Pumpable or manual application ▪ Levels and renovates old floors ▪ Rapid drying ▪ 4 hour walk on time [23 °C (73 °F)] ▪ Excellent underlay for tiles, sheet systems and wood floor bonding systems ▪ Excellent underlay for resin flooring ▪ Low odour ▪ May be used as a wearing surface

Technical Data	
Packaging	25 kg (55 lb) bag
Colour	Concrete Grey
Yield	Approx. 14 L (3.7 US gal.) (0.5 ft ³) per bag
	Approximate thickness per 25 kg (55 lb) bag
	5 mm (3/16 in) 2.8 m ² (30 ft ²)
	10 mm (3/8 in) 1.4 m ² (15 ft ²)
	16 mm (5/8 in) 0.88 m ² (9 ft ²)
	25 mm (1 in) 0.56 m ² (6 ft ²)
	(The above does not allow for surface porosity, profile or wastage).
Shelf Life	1 year in unopened packaging. Store dry at temperatures between 5 and 25 °C (41 and 77 °F) ensuring that product is not exposed to rain, condensation or high humidity.
Mix Ratio	4.25 L (1.12 US gal.) water per 25 kg (55 lb) bag
Properties at 23 °C (73 °F) and 50 % R.H.	
Density ASTM C185 (wet mix)	2.07 kg/L (129 lb/ft ³)
Application Temperature (substrate and ambient)	10 °C (50 °F) min., 25 °C (77 °F) max.
Application Thickness	5 mm (3/16 in) min. 25 mm (1 in) max.
Compressive Strength	
ASTM C109, ~MPa (~psi)	23 °C (73 °F)
24 hrs	18.8 (2727)
3 days	22.8 (3307)
7 days	24.5 (3553)
14 days	28 (4061)
28 days	31 (4496)
Setting Time ASTM C266	
Initial set	30 min
Final set	40 min
Flowability ASTM C230 (modified)	0 min 300 mm (11.8 in) 15 min 240 mm (9.45 in)
Working Time 25 mm (1 in) thickness	20 min

Overcoating	Water-based materials	8 h
	Solvent-free materials	24 h
	Solvent-based materials	36 h
Final Drying Time		
Foot traffic	4 h	
Lightly serviceable	1 day	
Fully serviceable	2 days	
Volume Change ASTM C531		
28 days	+ 0.036 %	
Pull-Out Strength (on concrete) CSA-A23.2-6B		
10 mm (0.39 in) thickness	2.50 MPa (362.6 psi) (substrate failure)	
25 mm (1 in) thickness	2.30 MPa (333.6 psi) (substrate failure)	
<i>Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.</i>		

HOW TO USE

Surface Preparation & Priming

The substrate must be dry, clean and stable before priming and applying the self-levelling screed material. Remove all existing treatments such as coatings, sealers, wax, latex compounds, impregnations and curing agents, together with all contaminants i.e. dirt, dust, laitance, grease, oils, and foreign matter, which will interfere with the penetration of Sika® Level-01 Primer^{CA} and the adhesion of Sikafloor® Level-25^{CA}.

Prepare concrete- and cement-based substrates by mechanical means, such as shotblasting, sandblasting, water-jetting, scarifying, or other appropriate methods, to achieve an open-textured, fine-gripping surface profile (ICRI / CSP 4 minimum). Weak concrete should be removed and surface defects such as blowholes and spalls fully exposed and repaired with a suitable Sika mortar prior to priming and levelling. All cracks and holes should be similarly filled to prevent seepage of the primer through to lower areas. Consult Sika Canada for recommendations.

All loose, friable material including preparation residue, must be completely removed using a vacuum before application of the Sika® Level-01 Primer^{CA}. The compressive strength of the concrete substrate should be at least 25 MPa (> 3625 psi) at 28 days with a minimum tensile strength of 1.5 MPa (218 psi) at the time Sika® Level-01 Primer^{CA} is applied. Moisture Vapour Emission Rates of the substrate should comply and meet the requirements of the proposed floor covering. Please consult the manufacturer of the final floor finish for advice.

Careful consideration should be given to the selection of the method of mechanical surface preparation and the timing of application of the primer and underlayment. Immediately following mechanical preparation on some excessively porous substrates, outgassing will increase for a short period of time (approx. 48 hours) until equilibrium in the slab vapor pressure and the ambient environment is reached. Before overall installation begins, Sika Canada recommends the application of several small test patches to determine primer application requirements and acceptability of final product performance. In general, a one-coat application of the Sika® Level-01 Primer^{CA} should be sufficient. However, allowance should be made for double priming on excessively porous substrates. Where multiple coats are required, do not apply excessive material.

Mixing	Add 4.25 L (1.12 US gal.) of potable water to a suitably sized mixing container and while mixing slowly add the powder (25 kg/55 lb). Once all the powder has been added continue mixing with a low speed electric mixer (300 - 400 rpm) for a minimum of three (3) minutes until a uniform mix has been achieved. Let material stand until the majority of air bubbles have dispersed.
Application	Pump: Use a conventional floor screed dual stage mixer and pump and control the water dosage to achieve a flowable consistency [4.25 L (1.12 US gal.) per 25 kg (55 lb)]. After pumping onto the pre-primed surface, spread by trowel or pin screed rake to the required thickness. Thoroughly spike roll in two directions (90°) to remove trowel marks and any entrapped air. Manual: Pour the mixed material onto the pre-primed surface and spread by trowel or pin screed rake to the required thickness. Thoroughly spike roll in two directions (90°) to remove trowel marks and any entrapped air.
Curing	Sikafloor® Level-25 ^{CA} must be allowed to air cure. Do not wet cure or use curing and sealing compounds.
Clean Up	Use water. Hardened material may have to be mechanically removed.
Limitations	<ul style="list-style-type: none"> ▪ Important: protect stored material from exposure to rain, condensation and high humidity as moisture may penetrate packaging, causing lumps. ▪ For best results, condition product to 18 to 29 °C (65 to 84 °F) prior to mixing and installation. Lower temperatures may result in slower strength development and longer cure times. ▪ Protect newly applied Sikafloor® Level-25^{CA} from condensation and water for at least 24 hours. ▪ Protect Sikafloor® from excess heat and moving air while curing. ▪ Turn off radiant heating and forced air ventilation systems for 24 hours. ▪ Do not exceed the recommended water dosage. ▪ Low temperatures extend drying times. ▪ Temperature variations will affect working time. ▪ Sikafloor® Level-25^{CA} does not provide an aesthetic finish.

- Not suitable for slopes or inclines > 0.5 %.
- For interior use only.
- When overcoating with Sikafloor® resins or any subsequent layers of Sikafloor® Level-25^{CA}, mechanical preparation is required to remove any surface laitance that could interfere with the bond.
- When overcoating Sikafloor® Level-25^{CA}, ensure the moisture content meets the requirements of the coating product.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent SAFETY DATA SHEET containing physical, ecological, toxicological and other safety-related data.

KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY

The Information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions, within their shelflife. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

SIKA CANADA INC.

Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9

Other locations
Toronto
Edmonton
Vancouver

1-800-933-SIKA
www.sika.ca

Certified ISO 9001 (CERT-0102780)
Certified ISO 14001 (CERT-0102791)

