



# PRODUCT DATA SHEET

## Sikasil® WS-295

STRUCTURAL GLAZING/WEATHER SEALING GRADE, NEUTRAL-CURE AND NO-BLEED SILICONE SEALANT

### PRODUCT DESCRIPTION

Sikasil® WS-295 is a versatile, one-component, non-sag, elastomeric, neutral-cure silicone sealant. It possesses a no-bleed formulation and is suitable for above grade, horizontal and vertical, interior or exterior applications, including structural glazing and weather sealing.

### WHERE TO USE

- Structural glazing\*
  - Conventional glazing
  - Perimeter sealing of windows, doors and skylights
  - Unitized curtain wall assembly and field installation
  - Panel stiffeners
  - Precast expansion joints
  - Weather sealing of most common building materials
- \* (requires written approval from Sika Canada Technical Services)

### CHARACTERISTICS / ADVANTAGES

- Structural glazing and weather sealing applications with one product
- May be applied in below freezing temperatures if substrates are completely dry, frost-free and clean.
- Excellent gunability in all temperatures.
- Adhesion to porous and non-porous materials, including glass, aluminium, metal, tile, fibreglass, plastic, ceramic, masonry, concrete, brick, powder coated aluminium, fluoropolymer painted surfaces, vinyl, PVC, granite, limestone, marble and wood
- Capable of accommodating ± 50 % joint movement
- Non-staining, maintains appearance of architectural substrates.
- Unaffected by most atmospheric conditions.
- Meets industry specifications: ASTM C920, Type S, Grade NS, Class 50/50, Use NT, M, G, A, O; ASTM C1184 Structural Silicone Sealant; TT-S-00230C, Type II, Class A; CAN/CGSB 19.13-M87, AAMA 802.3 Type II, AAMA 803.3, AAMA 805.2, AAMA 808.3 and California Air Resources Board 2003 requirements for VOC content.

### PRODUCT INFORMATION

|                           |   |
|---------------------------|---|
| <b>CSC MasterFormat®</b>  | <b>07 92 13 (08 85 00)   ELASTOMERIC JOINT SEALANTS</b>                               |
| <b>Packaging</b>          | 295 mL (10.1 US fl. oz) cartridge, 24/case<br>600 mL ( 20 US fl. oz) sausage, 20/case |
| <b>Colour</b>             | Aluminum, Black, Bronze, Colonial White, Limestone, Medium Bronze, White.             |
| <b>Shelf Life</b>         | 12 months in original unopened containers   |
| <b>Storage Conditions</b> | Store at or below +32 °C (90 °F).   |

## TECHNICAL INFORMATION

|                     |   |   |
|---------------------|---|---|
| Shore A Hardness    | 20                                      | (21 days at 25 °C (77 °F) (50 % R.H.) (ASTM C661)                                       |
| Tensile Strength    | 1.59 MPa (230 psi)                      | (21 days at 25 °C (77 °F) 50 % R.H.) (ASTM D412)  |
| Elongation at Break | 800 %                                   | (21 days at 25 °C (77 °F) 50 % R.H.) (ASTM D412)  |
| Adhesion in Peel    | 30 pli on aluminium, glass and concrete | (7 days at +25 °C (77 °F) 50 % R.H.) (ASTM C794)  |
| Movement Capability | +/-50 %                                 | (21 days at +25 °C (77 °F) and 50 % R.H.) (ASTM C719)                                   |
| Service Temperature | -62.2 °C to +176 °C (-80 °F to 350 °F)  |   |
| Extrusion Rate      | 150                                     | <b>Extrusion Rate g/min ASTM C1183 mod.</b><br>3 mm (1/8 in) orifice @ 0.6 MPa (90 psi) |

## APPLICATION INFORMATION

| Yield    | Linear meters per litre |       | Linear feet per cartridge |       |
|----------|-------------------------|-------|---------------------------|-------|
|          | Width<br>mm (in)        | Depth | Depth                     | Depth |
| 6 (1/4)  | 24.8                    |       | 24                        |       |
| 13 (1/2) | 12.4                    | 6.2   | 12                        | 6     |
| 19 (3/4) | 8.3                     | 4.1   | 8                         | 4     |

  

|                       |  |  |
|-----------------------|--|--|
| Sag Flow              | no sag   | (+25 °C (77 °F) 50 % R.H.) (ASTM C639) |
| Substrate Temperature | Sealant may be applied in below freezing temperatures, but surfaces must be dry, frost-free and clean. Sealant should be installed when the joint is at mid-range of its anticipated movement. |  |
| Curing Rate           | 3 mm (1/8 in) / 24 h   |  |
| Skimming time         | 25 minutes   |  |
| Tack-free time        | 50 minutes   | (ASTM C679)                            |

## BASIS OF PRODUCT DATA

Product properties are typically averages, obtained under laboratory conditions. Reasonable variations can be expected on-site due to local factors, including environment, preparation, application, curing and test methods.

Properties tested at 23 °C (73 °F) and 50 % R.H. unless stated otherwise.

## LIMITATIONS

- Requires written approval from Sika Canada Technical Services prior to use in structural glazing.
- The minimum sealant depth is 6 mm (1/4 in), the maximum is 13 mm (1/2 in).
- Do not apply when substrate temperatures are below -28 °C (-20 °F) or above +54 °C (130 °F).
- Lower temperature and humidity will extend tack free and cure rates.
- Do not apply to damp or wet surfaces.
- Substrates must be completely dry, frost-free, and clean.
- Do not apply to surfaces that are to be painted, as the sealant surface will not hold paint.
- Do not apply to substrates that bleed oil, plasticizers or solvent.
- Do not allow the uncured sealant to come in contact with solvent or curing polyurethanes.
- Avoid contact with materials or surfaces impregnated with, or containing oil, asphalt, tar, or bituminous materials.
- This material is not intended for immersion or

vehicular traffic.

- Brass and copper may be discoloured through contact: apply a sample prior to application.
- Test sensitive substrates, such as mirror backings, for compatibility before use.
- Allow treated wood to age for at least six (6) months before application of the sealant.

## ENVIRONMENT, HEALTH & SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

All joint surfaces must be clean, sound, dry, and frost free. Joint walls must be free of oils, asphalt, tar, bituminous materials, grease, paints, coatings or sealers. Curing compounds, release agent residues, glazing compounds, and any other foreign matter must be removed.

Porous substrates should be cleaned by mechanical methods, such as grinding, saw cutting, blast cleaning (sand or water), or wire brushing. Dust, loose particles, etc. should be blown out of joints with oil-free compressed air or vacuum cleaned to remove all material which may interfere with adhesion.

Non-porous substrates should be cleaned by using a solvent wipe method, applied by lint free and clean rags and allow the solvent to evaporate before installing the sealant. Xylene or an approved commercial solvent can be used, ensuring the solvent manufacturer's instructions are strictly followed. Soap or detergent and water cleaning treatments are not recommended.

Cleaning of all surfaces should be done just prior to the sealant application.

Apply Sikasil® WS-295 only to suitably prepared and cleaned substrates. Long term adhesion and performance is dependant upon such.

### Priming

Sikasil® WS-295 is designed to obtain adhesion without the use of a primer, however, certain substrates may require a primer. A field test is recommended to determine the adhesion of the sealant and/or primer and sealant combination, to confirm results and the

suitability of the proposed application. Consult Sikasil® Primer Data Sheets or contact Sika Canada for additional information on priming.

**NOTE:** Priming is never a substitute for proper surface cleaning and preparation.

### APPLICATION METHOD / TOOLS

For best performance Sikasil® WS-295 should be gunned into joints when the joint slot is at the mid-point of its designed expansion and contraction.

Do not open the product container until preparation and, where necessary, priming work has been completed.

When installing during time of large temperature fluctuations, such as spring or fall, and in joints designed for movement greater than  $\pm 25\%$ , be aware that significant joint movement before cure, may cause aesthetic issues such as ripples in the sealant surface. Performance will not be affected.

Apply the sealant using a professional caulking gun or dispensing equipment. Place the nozzle deep into the joint and gun with a steady and even flow of sealant preceding the nozzle to avoid air entrapment. Also avoid overlapping of the sealant as this also entraps air. Extrude in one continuous operation with consistent positive pressure to force the material into the joint.

Tool the sealant at once after application and before a skin forms (approximately 25 minutes). Tool to a concave shape and ensure adequate pressure to achieve maximum adhesion with the joint walls. Dry tooling is recommended.

**Note:** Do not use spray water or other liquids when tooling.

### CLEAN UP

Clean all tools and equipment and remove excess sealant from substrates, all while the material is uncured, using a commercial solvent, such as xylene. Strictly follow the manufacturer's instructions for use and warnings. Once hardened, product can only be removed mechanically.

## LOCAL RESTRICTIONS

### Product Data Sheet

Sikasil® WS-295

April 2022, Version 01.01

020511030000000009



Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: [www.sika.ca](http://www.sika.ca)

### **Sika Canada Inc.**

Head Office  
601, avenue Delmar  
Pointe-Claire, Quebec  
H9R 4A9  
1-800-933-SIKA  
[www.sika.ca](http://www.sika.ca)

### **Other locations**

Boisbriand (Quebec)  
Brantford; Cambridge;  
Sudbury; Toronto (Ontario)  
Edmonton (Alberta)  
Surrey (British Columbia)

### **Product Data Sheet**

Sikasil® WS-295  
April 2022, Version 01.01  
02051103000000009

